

9177

Elasta Patch Sandable Patching Compound

Description and Uses

Elasta Patch is a premium quality, sandable elastomeric patching compound for repairing cracks and holes up to 1/8" deep in wood or masonry surfaces.

- Sandable
- Adheres to Most Surfaces
- Produces a Thick, Tough, Elastic Patch
- Provides a non-penetrating seal against wind driven rain
- Water Based- Easy Water Clean-Up
- UV Resistant
- Low VOC/Environmentally Friendly
- Wood Surfaces
- Bridges Joints Between Wood, Masonry, and/or Metal Surfaces on Vertical Walls.
- Masonry Surfaces

Packaging

- Flat Sheen
- Brown Color
- Quarts, Gallons, 5 Gallons

Technical Information/Specifications

TYPE: Acrylic Resin

VISCOSITY: 135-140 KU'S @ 77°F

SOLIDS: 64-67% Weight
59-62% Volume

DILUENT: Water

FLASH POINT: N/A

V.O.C.: <50 grams per liter

DRY TO TOUCH: 30 Minutes

RECOAT: 12 Hours

CURE TIME: 3-5 Days

Limitations

- Do not install any product if the temperature is below 55°F.
- Rain may damage uncured products.
- Do not allow any non-applied product to FREEZE.
- DO NOT PAINT OVER MILDEW. Mildew is a fungus, brown, black, grey or even white in color, and will rapidly grow through any coating applied over it. A solution of 50% household bleach and 50% water will kill the mildew. Rinse thoroughly. See precautions on bleach label for handling before using.



Preparation & Application

Surface Preparation

- Remove all dirt, soot, rust, chalk, loose or peeling paint.
- Reset loose bricks and tuck mortar joints as necessary.
- Efflorescence must be removed by washing with a 10% solution muriatic acid.
- DO NOT APPLY OVER MILDEW. Mildew is living fungus, brown, black, grey or even white in color and will rapidly grow through any coating applied over it. Kill and remove by scouring and scrubbing with a solution of 50% household bleach and 50% water. Rinse thoroughly. Read precautions on label before using.
- Prime cracks and holes with Stretch-Guard® 7075 Primer before applying 9177 Elasta Patch.
- Prime bare wood surfaces with Life's 7075.

Application

- **CAUTION:** Do not apply when temperatures are below 50°F or expected to drop below 40°F within a 24 hour period or when fog or rain is in the 24 hour forecast.
- Use a 3" or 4" nylon bristle brush to patch minor cracks and holes. Forcing the material into the open space.
- Use a putty knife or trowel for large cracks or holes. Working in small areas, apply at a maximum of 1/8" thick.
- On cracks 1/32" or larger, bridge by reinforcing with Stretch-Guard® Seam Tape laid down while caulk is still wet.
- The overcoat with a second coat of caulk so tape is completely absorbed.
- Allow to dry 12 hours before applying top coat.
- Mil Film Thickness
 - At one gallon per 26 square feet
 - Wet 125 mils - Dry 54 mils
 - 13 Square feet at 1/8 inch thick.

Maintenance

- Clean up spilled and undried product immediately with water.
- Clean hands and skin with warm water and soap.
- **Repair:** Repairs may be done by removing the damaged area and replacing the material as written in this information guide.

