

3M™ Scotch-Weld™ Epoxy Adhesive 1751 B/A

Last Revision Date: December, 2009



Product Description

3M™ Scotch-Weld™ Epoxy Adhesive 1751 B/A is a gray, aluminum filled, two-part, room temperature curing structural adhesive.


Product Features

- Excellent adhesion to metals
- Good void filling properties
- Ideal for repairing holes, dents and cracks in metal


Technical Information Note


The following technical information and data should be considered representative or typical only and should not be used for specification purposes.


Typical Mixed Physical Properties


Property	Values	Additional Information
Open Time	45 min	View 

Notes: Maximum time allowed after applying adhesive to one substrate before bond must be closed and fixed in place. Cure times are approximate and depend on adhesive temperature. For hotmelts: The approximate bonding range of a 1/8" bead of molten adhesive on a non-metallic surface.

Worklife, 100g mixed	45 min	View 
Temp C: 23C Temp F: 73F		


Time to Handling Strength	8 to 12 hr	View 
Temp C: 23C Temp F: 73F		

Time to Full Cure	7 day	View 
Temp C: 23C Temp F: 73F		



Time to Full Cure	4 hr	View 
Temp C: 23C Temp F: 73F		

Notes: The cure time is defined as that time required for the adhesive to achieve a minimum of 80% of the ultimate strength as measured by aluminum-aluminum OLS.

Typical Physical Properties

Property	Values	Additional Information
Color	Gray	View 
Test Name: Cured		

Typical Uncured Physical Properties


Property	Values	Additional Information
Base Color	Gray	
Accelerator Color	Amber	
Base Viscosity	145 s	View 
Notes: Time to deliver 20 gms@ 50 psi thru a 0.10in orifice		
Accelerator Viscosity	125 s	View 
Notes: Time to deliver 20 gms@ 50 psi thru a 0.10in orifice		
Base Resin	Modified Epoxy	

Accelerator Resin	Modified Epoxy
Base Net Weight	10.8 lb/gal

Accelerator Net Weight	7.9 lb/gal
Mix Ratio by Volume (B:A)	3:2


Mix Ratio by Weight (B:A)	2:1



Typical Cured Characteristics

Property	Values	Additional Information
Shore D Hardness	77	View 
Test Method: ASTM D2240		

Temp C: 23C
Temp F: 73F

Typical Performance Characteristics

Property	Values	Additional Information
Overlap Shear Strength	2400 lb/in²	View 
Test Method: ASTM D1002		
Dwell/Cure Time: 7 Dwell Time Units: day Temp C: 23C Temp F: 73F Environmental Condition: 50%RH Substrate: Steel Surface Preparation: Solvent Wipe		
Notes: All aluminum data were developed on .063-inch thick 2024 T-3 clad aluminum and all steel data on .035-inch cold rolled steel. Test specimens were 1/2-inch overlap, 1-inch wide, pulled at a testing rate of .1-inch/min.		

T-Peel Adhesion 7day 23C FPL Etched Aluminum	4 lb/in width	View 
Test Method: ASTM D1876		
Test Name: T-Peel Adhesion Dwell/Cure Time: 7 Dwell Time Units: day Temp C: 23C Temp F: 73F Substrate: FPL Etched Aluminum		
Notes: 2 psi applied during dwell		
T-Peel Adhesion 7day 23C Steel	5 lb/in width	View 
Test Method: ASTM D1876		
Test Name: T-Peel Adhesion Dwell/Cure Time: 7 Dwell Time Units: day Temp C: 23C Temp F: 73F Substrate: Steel Surface Preparation: Solvent Wipe		
Notes: 2 psi applied during dwell		

Storage and Shelf Life

Store products at 60-80°F (15-27°C) for maximum storage life.
Rotate stock on a “first in-first out” basis. 3M™ Scotch-Weld™ Epoxy Adhesive 1751 B/A has a storage life of 24 months from date of manufacture in unopened containers.

Trademarks

3M and Scotch-Weld are trademarks of 3M Company.

Handling/Application Information

Directions for Use

- For high strength structural bonds, paint, oxide films, oils, dust, mold release agents and all other surface contaminants must be completely removed. The amount of surface preparation depends on the required bond strength and the environmental aging resistance desired by user. See surface preparation section.
- Use gloves to minimize skin contact with adhesive.
- This product consists of two parts. Mix thoroughly by weight or volume in the proportions specified in the Uncured Properties Section. Mix approximately 15 seconds

after a uniform color is obtained.

- 4. For maximum bond strength, apply product evenly to both surfaces to be joined.
- 5. Application to the substrates should be made within 45 minutes. Large quantities and/or higher temperatures will reduce this working time.
- 6. Join the adhesive coated surfaces and allow to cure at 60°F (16°C) or above until firm. Up to 200°F (93°C), will speed curing.
- 7. The following times and temperatures will result in a full cure:

Cure Temperature Time

75°F (24°C) 7 days

150°F (67°C) 120 minutes

200°F (93°C) 30 minutes

- 8. Keep parts from moving until handling strength is reached. Contact pressure is necessary. Maximum shear strength is obtained with a 3-5 mil bond line.
- 9. Excess uncured adhesive can be cleaned up with ketone type solvents.* Adhesive coverage: A 0.005 in thick bondline will yield a coverage of 320 sqft/gallon.

*Note: When using solvents, extinguish all ignition sources and follow manufacturer’s precautions and directions for use.

Surface Preparation

For high strength structural bonds, paint, oxide films, oils, dust, mold release agents and all other surface contaminants must be completely removed. The amount of surface preparation depends on the required bond strength and the environmental aging resistance desired by user.

The following cleaning methods are suggested for these common surfaces:

Steel:

- 1. Wipe free of dust with oil-free solvent such as acetone, isopropyl or alcohol solvents.*
- 2. Sandblast or abrade using clean fine grit abrasives.
- 3. Wipe again with solvent to remove loose particles.
- 4. If a primer is used, it should be applied within 4 hours after surface preparation.

*Note: Read and follow component supplier’s environmental, health and safety recommendations prior to preparing this etch solution.

Aluminum:

- 1. Vapor Degrease: Perchloroethylene condensing vapors for 5-10 minutes.*
- 2. Alkaline Degrease: Oakite 164 solution (9-11 oz./gallon water) at 190°F ± 10°F (88°C ± 5°C) for 10-20 minutes. Rinse immediately in large quantities of cold running water.
- 3. Acid Etch: Place panels in the following solution for 10 minutes at 150°F ± 5°F (66°C ± 3°C).

Sodium Dichromate 4.1-4.9 oz./gallon

Sulfuric Acid, 66°Be 38.5-41.5 oz./gallon

2024-T3 aluminum (dissolved) 0.2 oz./gallon minimum

Tap Water as needed to balance

- 4. Rinse: Rinse panels in clean running tap water.
- 5. Dry: Air dry 15 minutes; force dry 10 minutes at 190°F (88°C) ± 10°F (5°C).
- 6. If primer is to be used, it should be applied within 4 hours after surface preparation.

Plastics/Rubber

- 1. Wipe with isopropyl alcohol.*
- 2. Abrade using fine grit abrasives.
- 3. Wipe again with isopropyl alcohol.*

Glass

- 1. Solvent wipe surface using acetone or methyl ethyl ketone (MEK).*
- 2. Apply a thin coating (0.0001 in. or less) of primer such as 3M™ Scotch-Weld™ Structural Adhesive Primer EC-3901 to the glass surfaces to be bonded and allow the primer to dry before bonding.

*Note: When using solvents, extinguish all ignition sources and follow manufacturer’s precautions and directions for use

References

Property	Values
3m.com Product Page	https://www.3m.com/3M/en_US/company-us/all-3m-products/~ /3M-Scotch-Weld-Epoxy-Adhesive-1751/?N=5002385+3293242441&rt=rud
Safety Data Sheet SDS	https://www.3m.com/3M/en_US/company-us/SDS-search/results/?gsaAction=msdsSRA&msdsLocale=en_US&co=ptn&q=1751 B/A

ISO Statement

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

Precautionary Information

Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. For additional health and safety information, call 1-800-364-3577 or (651) 737-6501.

Information

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M’s control and uniquely within user’s knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer’s application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M’s option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

Disclaimer: 3M industrial and occupational products are intended, labeled, and packaged for sale to trained industrial and occupational customers for workplace use. Unless specifically stated otherwise on the applicable product packaging or literature, these products are not intended, labeled, or packaged for sale to or use by consumers (e.g., for home, personal, primary or secondary school, recreational/sporting, or other uses not described in the applicable product packaging or literature), and must be selected and used in compliance with applicable health and safety regulations and standards (e.g., U.S. OSHA, ANSI), as well as all product literature, user instructions, warnings, and limitations, and the user must take any action required under any recall, field action or other product use notice. Misuse of 3M industrial and occupational products may result in injury, sickness, or death. For help with product selection and use, consult your on-site safety professional, industrial hygienist, or other subject matter expert. For additional product information, visit www.3M.com.