EUCO QWIKJOINT 200



POLYUREA FLOOR JOINT FILLER

DESCRIPTION

EUCO QWIKJOINT 200 is a fast-setting, semi-rigid polyurea used for filling control and construction joints in industrial concrete floors. EUCO QWIKjoint 200 represents a new generation of polyurea technology with features and benefits unlike any other polyurea joint filler on the market. Among these benefits are a super-fast set time and an extended shave time: EUCO QWIKjoint 200 can be trimmed flush with the floor immediately after placement or up to 24 hours later. EUCO QWIKjoint 200 supports and protects joint edges from heavy loads and wheel traffic, reducing spalling of the joint edges.

PRIMARY APPLICATIONS

- Concrete construction and control joints
- Crack repair for old floors

- · Industrial and commercial floors
- Freezer floors

FEATURES/BENEFITS

- · Fast-setting formula reduces downtime
- · Large shave time window allows for greater flexibility in scheduling joint filling operations
- · No bubbles no foaming when used in damp joints
- Tough performance reduces floor joint repairs and maintenance
- Suitable for filling cracks in older floors to reduce the rate of joint deterioration
- Will cure in temperatures as low as -20° F (-29°C)
- · Less moisture-sensitive than standard polyureas

TECHNICAL INFORMATION

Typical Engineering Data

The following are typical values obtained under laboratory conditions. Expect reasonable variation under field conditions.

PROPERTY	TEST METHOD	RESULT	
Gel Time		25 seconds	
Shore D Hardness	ASTM D2240	34 to 36	
Shore A Hardness	ASTM D2240	84 to 88	
Tensile Strength @ 7 days	ASTM D412	660 psi (4.6 MPa)	
Elongation @ 7 days	ASTM D412	220% to 260%	
Shave "Window"		30 min to 24 hours	
Tack-Free Time		1 to 3 minutes	
Traffic Ready Time		Light Traffic: 15 min Heavy Traffic: 30 min	

Chemical Ratings: Excellent - no effect after 2 weeks

Good - no effect for 24 hours **Poor -** affected within 24 hours

CHEMICAL RESISTANCE, ASTM D1308					
Acetic Acid, 5%	excellent				
Alcohol, 10%	excellent				
Alkalies	excellent				
Ammonium Hydroxide, 10%	excellent				
Brake Fluid	good				
Diesel Fuel	excellent				
Ethylene Glycol (antifreeze)	good				
Gasoline	excellent				
Hydrochloric Acid, 20%	excellent				
JP-4 Jet Fuel	excellent				
Used Motor Oil	excellent				
Salt Water	excellent				
Sodium Hydroxide, 10%	excellent				
Sulfuric Acid, 10%	good				
Xylene	poor				

Appearance: EUCO QWIKjoint 200 is available in Standard Gray only. The product may discolor over time if exposed to either natural or artificial ultraviolet light. If aesthetics are an important issue or if another color is desired, use EUCO QWIKjoint UVR, which is UV resistant and available in 33 standard colors.

PACKAGING

EUCO QWIKjoint 200 is a two-component product packaged in 10 gal (37.9 L) and 100 gal (379 L) kits. 22 oz (600 mL) side-by-side cartridges are packaged 12 per case. Each cartridge yields 40 in³ (655 cm³). The mix ratio for all packaging sizes is 1:1.

SHELF LIFE

1 year in original, unopened containers

SPECIFICATIONS/COMPLIANCES

EUCO QWIKjoint 200 complies with ACI 302 performance recommendations regarding control and construction joint fillers.

Canadian Food Inspection Agency Compliant

COVERAGE

1 gallon (3.78 L) of EUCO QWIKjoint 200 yields 231 in³ (3,785 cm³) of material.

Six 22 oz (600 mL) cartridges equal approximately 1 gallon (3.78 L) of material.

The following table gives rough guidelines on estimating the amount of material needed. These numbers represent the length of joint that can be filled with 1 gallon (3.78 L) of material, based on the joints' width and depth.

	1"	1.5"	· 2"	2.5"	3"
Joint Width					
3/32" (2.4 mm)	205 ft (62.5 m)	136 ft (41.5 m)	102 ft (31.1 m)	82 ft (25.0 m)	68 ft (20.7 m)
1/8" (3.2 mm) [^]	154 ft (46.9 m)	102 ft (31.1 m)	77 ft (23.5 m)	61 ft (18.6 m)	51 ft (15.5 m)
3/16" (4.8 mm)	102 ft (31.1 m)	68 ft (20.7 m)	51 ft (15.5 m)	41 ft (12.5 m)	34 ft (10.4 m)
1/4" (6.4 mm) ´	77 ft (23.5 m)	51 ft (15.5 m)	38 ft (11.6 m)	30 ft (9.1 m)	25 ft (7.6 m)
3/8" (9.5 mm)	51 ft (15.5 m)	34 ft (10.4 m)	25 ft (7.6 m)	20 ft (6.1 m)	17 ft (5.2 m)
1/2" (12.7 mm)	38 ft (11.6 m)	25 ft (7.6 m)	19 ft (5.8 m)	15 ft (4.6 m)	12 ft (3.7 m)

DIRECTIONS FOR USE

Surface Preparation: All joints to be filled must be clean and dry. All oil, dirt, debris, paint and any other material that may be a bond breaker must be removed. The final step in cleaning must be the complete removal of all residue by use of oil-free compressed air, or by re-cutting the joint, followed by vacuuming. All joint facings must possess an open surface texture with all curing compounds and sealers removed. If this product will be used for filling floor cracks, the cracks must be routed out and cleaned before filling. For proper installation, all edges must be squared off.

Joint Backing: To provide proper load transfer, EUCO QWIKjoint 200 must be filled full depth of the joint or crack. Do not use backer rod or other fill material for the purpose of reducing volume. Dried silica sand, 1/16" to 1/8" (1.5 to 3 mm), may be used to fill the crack at the bottom of the joint to prevent materal loss through the slab.

Priming: EUCO QWIKjoint 200 does not require a primer before application.

Preparation of 10 gal (37.9 L) units

Mixing: Due to its extremely fast set time, EUCO QWIKjoint 200 requires machine mixing and placing. **Slowly pre-mix Part B separately before using with a slow speed drill and mixing paddle for 2 to 3 minutes. Do not whip air into the Part B while mixing. Follow mechanical pump manufacturer's equipment instructions for operation.

NOTE: If EUCO QWIKjoint 200 is to be stored in the dispensing pump overnight, place a sheet of plastic wrap directly on top of the liquid material in each tank to prevent exposure to air.

Preparation of 22 oz (600 mL) cartridges

QWIKjoint 200 cartridges must be shaken well before opening and using, as some settlement is normal during storage. Remove the threaded cartridge nut, then remove the white plastic plug from the top of the cartridge. The nut and plug can be set aside and later used to re-seal a partially used cartridge. To avoid cross contamination during re-sealing, clean the white plastic plug prior to re-inserting in the top of the cartridge. Thread the included static mixing nozzle onto the cartridge securely. Load the cartridge into a 1:1 ratio, dual-component dispensing gun, designed to accommodate 600 mL (300 mL x 300 mL) cartridges. Hold the gun with the mixing nozzle pointing straight upward, and pump EUCO QWIKjoint 200 up to the top of the static mixing nozzle. Then, tilt the gun downward and dispense the first 2 to 3 pumps (or until material appears uniform) of material into a disposable container. Discard this material. The cartridge is now prepared for the placement of EUCO QWIKjoint 200.

Placement for 10 gal (37.9 L) units and 22 oz (600 mL) cartridges

EUCO QWIKjoint 200 must be installed in the joint full depth. Joints should be slightly overfilled and shaved smoothly with the surrounding joint edges, giving the floor joints a flat appearance. Shaving of excess EUCO QWIKjoint 200 can begin approximately 1 hour after placement, and up to 24 hours later, depending on jobsite conditions such as the concrete and ambient temperatures.