

Elastomeric Sheeting Uncured Neoprene Sheeting

Product Description

Tremco® Elastomeric Sheeting is a thermoset material made of the highest quality uncured neoprene rubber at a thickness of 60 mils (1.52 mm).

Basic Uses

Tremco Elastomeric Sheeting is designed to provide a durable, flexible, tearresistant bridge in areas of high movement such as expansion joints, construction joints and flashing where a membrane waterproofing such as TREMproof® 6100, TREMproof 201/60 or TREMproof 250GC is being used.

Availability

Immediately available from your local Tremco Sales Representative or Tremco Distributor. For Distributor locations visit www.tremcosealants.com.

Packaging

6" x 100' (151 mm x 30.6 M)

- 12" x 100' (300 mm x 30.6 M) 18" x 100' (450 mm x 30.6 M)
- 24" x 100' (604 mm x 30.6 M)
- 36" x 100' (906 mm x 30.6 M)

Installation

Rout out any construction joint filler to a depth of 1/2" (12.7 mm) and install open-cell polyurethane backer rod such that it protrudes to a height of 1/2" (12.7 mm), minimum.

Bond Tremco Elastomeric Sheeting a minimum 3" (10.2 cm) to either side of joint using TREMproof 6100, TREMproof 201/60 or TREMproof 250GC. Tremco Elastomeric Sheeting must be looped to a height/depth equal to the total anticipated movement. Overlap adjacent sheeting a minimum of 6" (15.3 cm).

Limitations

Not for use as a primary waterproofing membrane.

Warranty

Tremco warrants its Products to be free of defects in materials, but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Tremco makes no other warranty, expressed or implied, including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE, with respect to Tremco Products. Tremco's sole obligation shall be, at its option, to replace or to refund the purchase price of the quantity of Tremco Product proven to be defective, and Tremco shall not be liable for any loss or damage.

Please refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.

NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of

TYPICAL PHYSICAL PROPERTIES		
PROPERTY	TEST METHOD	TYPICAL VALUES
Thickness, Inches	ASTM D412	Gauge +/- 10%
Width, Inches	ASTM D751	Size +/- 1/8", -0
Length, Feet	ASTM D751	Size +/- 1", -0
Tensile Strength	ASTM D412 DIE C	1340
Elongation	ASTM D412 DIE C	400
Modulus, 100% Min %	ASTM D412 DIE C	24 to 75 %
Tear Resistance lb/in min	ASTM D624 DIE C	125
Brittleness Point at -40 °F	ASTM D2137	Does not break
Ozone Resistance 168 hr/100pphm/104 °F/50%EXT	ASTM D1149	No cracks at 7x
Water Absorption, Maximum Mass % 166 hr at 158 °F	ASTM D471	+8.5



3735 Green Rd Beachwood OH 44122 216.292.5000 / 800.321.7906 1451 Jacobson Ave Ashland OH 44805 419.289.2050 / 800.321.6357

Tremco Commercial Sealants & Waterproofing 220 Wicksteed Ave Toronto ON M4H1G7 416.421.3300 / 800.363.3213

1445 Rue de Coulomb Boucherville QC J4B 7L8 514.521.9555

www.tremcosealants.com

