



MiraFlor CQ Clear

Product Technical Data Sheet

MiraFlor CQ Clear is a two-component, high solids, medium viscosity clear resinous epoxy coating designed for use in multiple types of flooring applications. It can be installed neat as a high build protective floor coating or with the addition of broadcast aggregates and vinyl flakes for slip resistant decorative floor applications.

Once applied and upon full cure, *MiraFlor CQ Clear* provides a non-blushing concrete protective coating exhibiting excellent physical properties, flexibility and good chemical and abrasion resistance. If desired, it can be pigmented in the field utilizing Miracote ColorPax-E.

WHERE TO USE

- High build concrete vapor barrier protective coating.
- Seamless flooring applications.
- Aircraft, aeronautical and automotive facilities.
- Manufacturing and warehouse facilities.
- Secondary containment structures.
- Transportation terminals and loading docks.
- Restrooms and cafeterias.
- Hospitals and healthcare facilities.
- Prisons and correctional institutions.
- Stadiums and arenas.
- Decorative flooring treatments.

ADVANTAGES

- High build and medium viscosity floor coating.
- Functions well as concrete primer.
- Good chemical resistance.
- Good abrasion resistance.
- High solids content.
- Low odor during installation.
- Factory pigmented and color matching availability.
- USDA compliant.

THEORETICAL COVERAGE RATES

110 – 225 sq. ft. @ per gallon. (7-15 WFT)

PACKAGING and COLORS

Kit Sizes: 1.5-gallon, 3-gallon, 15-gallon

Component A: 1-gal, 2-gal, 5-gal units

Component B: .5-gal, 1-gal, 5-gal units

Available in clear and nine standard colors

Refer to Miracote Standard Color Chart E-U-W

Custom colors available – Minimum order quantities may apply.

MIX RATIO

Comp. A to Comp. B = 2:1 by volume.

SHELF LIFE AND STORAGE

One year from the date of manufacture as long as containers remain unopened and material is stored in a protected environment free from moisture, excessive heat, freezing temperatures, and direct sunlight.

TYPICAL PHYSICAL PROPERTIES @ 75°F (24°C)

Viscosity (mixed).....	600-700 cps
Solids Content.....	99%
Pot Life 50% RH (1-gallon mass)	Approximately 20 minutes
Dry Time 50% RH Tack Free	8 to 10 hrs.
	Light Traffic.....10-12 hrs.
	Normal Traffic.....12-24 hrs.
	Vehicular Traffic....24-36 hrs.
Recoat Time.....	8-24 hrs.
Compressive Strength ASTM D695	12,000 psi
Tensile Strength ASTM D638	4,400 psi
Adhesion ASTM D4541	> 400 psi (100% cohesive failure in concrete)
Hardness ASTM D2240, Shore D	75-80
Water Absorption Mil-D-3134.....	<1%
Microbial Resistance ASTM G21	Passes Rating 1
Fire Retardance	
ASTM E648, FTMS 372, NFPA 253, NBSIR 75-950	
Critical Radiant heat Flux	>1.07 Watts/cm ²

OVERVIEW OF INSTALLATION STEPS

• **Surface Preparation** – All surfaces must be clean, sound, dry and free from any bond inhibiting substances including, but not limited to, grease, oil and any other contaminants or loosely adhered materials. For concrete substrates, a minimum surface profile of a CSP-2 or higher is required depending on overall substrate conditions, coating requirements, and application thickness.

• **Mixing** – *MiraFlor CQ Clear* epoxy components must be mixed mechanically using a low-speed drill (300-450 rpm) until well blended with a “Jiffy-type” or similar Miracote-approved mixing paddle. Empty entire contents of component A and component B into a clean mixing vessel. Mix for approximately 3 minutes keeping the mixing head fully immersed at all times. At least once while mixing, stop to scrape down the sides and bottom of the pail to ensure thorough blending of both components. If not mixing full units, each component must be pre-mixed individually ensuring uniformity prior to use. Once completely mixed and in observance of pot life, dispense material immediately from the pail to the substrate.

Application – Pour out mixed *MiraFlor CQ Clear* in a large ribbon across the properly primed concrete surface or other type of substrate. Spread evenly with a flat squeegee, and back-roll with a high quality, phenolic core, industrial grade 3/16” to 1/4” maximum nap roller to achieve mil consistency. Consider use of roller cage end caps for precision gauging millage and minimal waste.

MiraFlor CQ Clear

Product Technical Data Sheet

FOR BEST RESULTS

- Always install a minimum 4' by 4' test area site mock-up for approval of acceptable color, texture, finish, adhesion, and any other critical requirement acceptable to the owner prior to proceeding with the installation.
- Verify and download current versions of product technical data sheets (PTDS), material safety data sheets (MSDS), and installation guides (IG) at www.miracote.com.
- Protect materials at all times from excessive heat and cold, and pre-condition to room temperature as necessary.
- Regularly check wet film thickness with mil gauge and monitor consumption to ensure correct application rates are obtained.
- The proper application of this product is the sole responsibility of the end user. Job site visits by Miracote representatives are only for the purpose of making recommendations, and do not assume any liability for supervision or quality control.
- Measure ambient temperature to ensure the material is only applied between a minimum of 45° F and a maximum of 90° F during placement and cure time.
- Measure substrate temperature to ensure the material is only applied between a minimum of 50° F and a maximum of 90° F during placement and cure time.

LIMITATIONS

- Installed product forms a vapor barrier after cure.
- Not intended for use on exterior concrete slabs-on-grade.
- Minimum ambient/substrate temperature of 50°F (10°C).
- Concrete must be minimum age of 21-28 days, depending on curing and drying conditions.
- Color may yellow over time when exposed to UV.
- Maximum allowable moisture vapor transmission (MVT) of 3.0 lbs./1000 sf./per 24 hr. period per ASTM F1869 (CaCl Testing).
- Maximum allowable moisture vapor transmission (MVT) of 75% RH as per ASTM F2170 (RH-Relative Humidity Testing).
- Use MiraPrime MVERS Plus epoxy moisture mitigation primer over concrete substrates that have MVT emissions that exceed these limits.

LIMITED WARRANTY

NO WARRANTY SHALL BE EFFECTIVE UNTIL THE TERMS AND CONDITIONS OF SALE SET FORTH IN CROSSFIELD PRODUCTS CORP. INVOICES ARE MET.

Crossfield Products Corp. warrants to the purchaser of its products that such products are free from manufacturing defect. Crossfield does not warrant or guarantee the workmanship performed by any person or firm installing its products. Crossfield's obligation under this warranty is limited solely to the original purchaser and solely to the remedy of replacement in kind of any product which Crossfield sold which may prove defective in manufacture within one year from date of installation, provided said product was stored correctly and installed within the product's shelf life, by the original purchaser and which Crossfield's examination shall disclose to Crossfield's satisfaction to be thus defective.

IN NO EVENT SHALL CROSSFIELD PRODUCTS CORP. BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES. THIS WARRANTY IS EXPRESSLY GIVEN IN LIEU OF ALL OTHER WARRANTIES EXPRESSED OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR USE AND ALL OTHER OBLIGATIONS OR LIABILITIES ON CROSSFIELD'S PART, AND WE NEITHER ASSUME NOR AUTHORIZE ANY PERSON OR PERSONS TO ASSUME FOR US ANY OTHER LIABILITY IN CONNECTION WITH SALE OF A CROSSFIELD PRODUCT. THIS WARRANTY SHALL NOT APPLY TO ANY OF CROSSFIELD'S PRODUCTS, WHICH HAVE BEEN SUBJECT TO ADULTERATION, ALTERATION ABUSE OR MISUSE. CROSSFIELD PRODUCTS CORP. MAKES NO WARRANTY WHATSOEVER IN RESPECT TO ACCESSORIES, PARTS OR MATERIAL NOT SUPPLIED BY CROSSFIELD PRODUCTS CORP., WHICH ARE USED IN CONNECTION WITH ITS PRODUCTS. THE TERM "ORIGINAL PURCHASER" IN THIS WARRANTY MEANS THAT PERSON, CORPORATION OR ENTITY TO WHOM CROSSFIELD PRODUCTS CORP. SOLD ITS PRODUCTS. ANY ACTION TO ENFORCE ANY WARRANTY OR FOR BREACH OF CONTRACT OR ARISING OUT OF ANY CLAIM AGAINST CROSSFIELD PRODUCTS CORP. SHALL BE COMMENCED AND MAINTAINED ONLY IN A COURT OF COMPETENT JURISDICTION IN THE CONTINENTAL UNITED STATES OF AMERICA. THE PURCHASER ACCEPTS THESE TERMS AND CONDITIONS, AND HEREBY EXPRESSLY WAIVES ANY CLAIM TO ADDITIONAL DAMAGES.

CAUTION: ALWAYS KEEP OUT OF THE REACH OF CHILDREN.



Miracote Product Line
Crossfield Products Corp

www.miracote.com

East Coast Office
140 Valley Road
Roselle Park, NJ 07204
P: (908) 245-2808
F: (908) 245-0659

West Coast Office
3000 E. Harcourt Street
Rancho Dominguez, CA 90221
P: (310) 631-6594
F: (310) 886-9119



MIRAFLOR CQ CLEAR
9-20-2021