



**PROSOCO**®

You. Us. The project.

# SL100 Water Repellent


PROSOCO® SL100 is a modified, “neat” silane system that offers invisible protection and low volatility. SL100 protects horizontal and vertical concrete and masonry surfaces against water and waterborne contaminants. The small molecular structure ensures maximum penetration and colorless protection of dense, color-sensitive surfaces. Ideal for GFRC, integrally colored precast concrete and many types of natural stone.

The absence of a solvent carrier enables applicators to achieve up to 5 times the coverage rate normally achieved with solvent-reduced protective treatments. Depth of penetration is controlled by the application rate (loading rate).

## SAFETY INFORMATION

Always read full label and SDS for precautionary instructions before use. Use appropriate safety equipment and job-site controls during application and handling.

**24-Hour Emergency Information:**  
INFOTRAC at 800-535-5053

	
<b>SEALANT • WATERPROOFING &amp; RESTORATION INSTITUTE</b>	
Issued to: PROSOCO Inc.	
Product: PROSOCO® SL100 Water Repellent	
ASTM D 6532: Water Absorption Reduction – Mortar 98.37%	
ASTM C 67: Water Absorption Reduction – Brick 96.35%	
ASTM C 140: Water Absorption Reduction – CMU 93.64%	
ASTM D 6490: Water Vapor Transmission WVT (grains/h ft <sup>2</sup> ) 1.32; Permeance 3.21	
Validation Date: 2/6/18 – 2/5/23	
No. 218-SL100223	Copyright © 2018
<b>CLEAR PENETRATING VERTICAL WATER REPELLENT VALIDATION PROGRAM</b>	
www.swrionline.org	

**NOTE:** The SWR Institute Validation Program uses standardized testing for validation purposes, including testing on CMU. PROSOCO does not recommend the use of SL100 on CMU.

## ADVANTAGES

- Long-lasting protection.
- Does not form a film or gloss.
- Compatible with lithium silicate hardeners/densifiers.
- Treated surfaces “breathe” – does not trap moisture.
- Forms an effective chloride screen that reduces surface erosion and corrosion of rebar in reinforced concrete caused by water and water-carried salts.
- Leaves little or no residue on clean window glass. Always test.
- Safe for use on surfaces subjected to vehicle traffic.
- Suitable for application on cured, cured & honed, and cured & polished concrete.
- CALGreen compliant.

## Limitations

- Not suitable for asphalt or other non-masonry materials.
- Not effective on limestone or marble. Always test natural stone to ensure desired results.
- Do not apply over Consolideck® LSGuard®.
- Not recommended for below-grade applications or for use under hydrostatic pressure.
- Will not prevent water penetration through structural cracks, defects or open joints.
- Not available in South Coast Air Quality Management District, except in regulation-exempt small container sizes.

## REGULATORY COMPLIANCE

### VOC Compliance

PROSOCO® SL100 Water Repellent is compliant with the US Environmental Protection Agency’s AIM VOC regulations.

Visit [www.prosoco.com/voc-compliance](http://www.prosoco.com/voc-compliance) to confirm compliance with individual district or state regulations.

# Product Data Sheet

## PROSOCO® SL100 Water Repellent

### TYPICAL TECHNICAL DATA

<b>FORM</b>	Clear, slightly yellow liquid Slight alcohol odor
<b>SPECIFIC GRAVITY</b>	0.92 – 0.93
<b>pH</b>	not applicable
<b>WT/GAL</b>	7.65 – 7.70 lbs
<b>ACTIVE CONTENT</b>	98%
<b>TOTAL SOLIDS</b>	62% ASTM D 5095
<b>VOC CONTENT</b>	350 g/L maximum Reactive Penetrating Sealer
<b>FLASH POINT</b>	>113° F (>45° C) ASTM D 3278
<b>FREEZE POINT</b>	no data
<b>SHELF LIFE</b>	1 year in tightly sealed, unopened container

### PREPARATION

Protect people, vehicles, property, plants and all non masonry surfaces from product, splash, residue, fumes, mists and wind drift. Divert and/or protect auto and pedestrian traffic.

Ensure fresh air entry and cross ventilation during application and drying. Extinguish all flames, pilot lights and other potential sources of ignition during use and until all vapors are gone. When applying to exteriors of occupied buildings, make sure all windows, exterior intakes and air conditioning vents are covered and air handling equipment is shut down during application and until all vapors have dissipated.

If possible, install all caulking, patching and joint sealants before application. If impractical, test for adhesion and grind joints as required to properly prepare for caulking, etc.

Surfaces should be thoroughly clean and free of dust, surface dirt, oil, grease and other contaminants that might prevent penetration. Carefully inspect for dust, dirt, moisture or other contaminants that can cause the product to react and stain the material.

The top of walls need to be capped and made watertight prior to application.

New concrete should be thoroughly cured before application. Surfaces to be treated may be damp but should be absorbent for good penetration.

**Specifier's Note – Curing New Concrete:** Blanket or water curing is recommended whenever possible. If a chemical curing agent is to be used during installation of new concrete, a test area

is recommended just before general application to ensure compatibility. Dissipating-type curing agents are recommended. Do not over apply the curing agent. Removal of all surface films and contaminants is necessary for best performance.

**NOTE:** Some floor and wall systems incorporate asphaltic or other crack-suppression membranes. This deeply penetrative protective treatment may penetrate through exposed stone, tile, grout or paver surfaces and react with the membrane to mobilize objectionable staining. Always pretest to ensure desired results.

### Surface and Air Temperatures

For maximum effectiveness, surface and air temperatures should be above 40°F (4°C) and below 95°F (35°C). Application on windy days may cause rapid evaporation and should be avoided.

**Recommended for these substrates. Always test. Coverage is in sq.ft./m. per gallon.**

<i>Substrate</i>	<i>Type</i>	<i>Use?</i>	<i>Coverage</i>
<b>Concrete*</b>	Brick	yes	150–400 sq.ft. 14–37 sq.m.
	Tile	yes	
	Precast Panels	yes	
	Pavers	yes	
<b>Fired Clay*</b>	Brick	yes	200–500 sq.ft. 19–46 sq.m.
	Tile	yes	
	Terra Cotta	yes	
	Pavers	yes	
<b>Marble, Travertine, Limestone</b>	Polished	no	N/A
	Unpolished	no	N/A
<b>Granite</b>	Polished	yes	1000–1500 sq.ft. 93–139 sq.m.
	Unpolished	yes	300–500 sq.ft. 28–46 sq.m.
<b>Sandstone*</b>	Unpolished	yes	200–400 sq.ft. 19–37 sq.m.
<b>Slate</b>	Unpolished	yes	300–600 sq.ft. 28–56 sq.m.

\*May have limited effectiveness on highly porous or neutral pH surfaces.

**Always test to ensure desired results.**

**Coverage estimates depend on surface texture and porosity.**

# Product Data Sheet

## PROSOCO® SL100 Water Repellent

### Equipment

Recommended application is by high volume, low-pressure (<50 psi) spray equipment. Fan spray tips are recommended.

Battery powered pump sprayers should be rated as explosion proof. Sprayers should be fitted with solvent-resistant hoses and gaskets to avoid discoloration.

Brushes and rollers may not achieve a uniform, extended coverage rate on large-scale applications, which could reduce cost efficiency. For small scale application, or when spray application is not appropriate, product may be applied using brush or roller. Contact Customer Care or your local PROSOCO representative for more information before use.

### Storage and Handling

Store in a cool, dry place away from potential ignition sources. Keep tightly closed when not dispensing. Do not alter or mix with other chemicals. Published shelf life assumes upright storage of factory-sealed containers in a dry place. Maintain temperature of 45–100°F (7–38°C). Do not double stack pallets. Dispose of unused product and container in accordance with local, state and federal regulations.

## APPLICATION

Read “Preparation” and the Safety Data Sheet before use.

**ALWAYS TEST** a small area of each surface to confirm suitability, coverage rates and desired results before starting overall application. Include in the test area any previous repairs and patches, including aesthetic cementitious finishes. Different surface compositions may result in absorption and/or appearance differences. Test with the same equipment, recommended surface preparation and application procedures planned for general application. Let surface dry thoroughly before inspection.

### Dilution & Mixing

Apply as packaged. Do not dilute or alter, or use for purposes other than specified.

### Application Instructions

#### *Horizontal Surfaces*

Apply once using enough material to keep the surface wet approximately 30 to 60 seconds before penetrating. Broom out puddles until they completely penetrate the surface.

#### *Vertical Surfaces*

Saturate surface in a single application. Use enough to thoroughly wet the surface. Thoroughly brush heavy runs and drips into the surface.

#### *Dense Surfaces*

On dense surfaces apply a single coat. Use enough to completely wet the surface without creating drips, puddles or rundown. Do not over apply. Test for application rate.

#### *Second Coat Application*

A second application may be needed on some porous surfaces. Apply the second coat a few minutes after the first coat has penetrated and appears dry. SL100 may have limited effectiveness on highly porous surfaces. Always test.

### Drying Time

Protect treated surfaces from rain, foot and vehicular traffic for at least 4 hours after application. SL100 gains its water-repellency properties in 72 hours.

### Cleanup

Clean tools and equipment immediately with mineral spirits, denatured alcohol or equivalent cleaning solvent. Remove rundown and spills as soon as possible.

### Maintenance

Remove surface dust and debris daily using a microfiber pad or dry dust mop.

Acid concentrates and acidic foods may etch the floor and leave a residual stain. Remove spills or stains from surfaces treated with SL100 as soon as possible to minimize any potential for damage. Do not use acidic cleaners.

For problem soiling or staining contact PROSOCO at 800-255-4255 for free consultation.

# Product Data Sheet

## PROSOCO® SL100 Water Repellent

### WARRANTY

The information and recommendations made are based on our own research and the research of others, and are believed to be accurate. However, no guarantee of their accuracy is made because we cannot cover every possible application of our products, nor anticipate every variation encountered in masonry surfaces, job conditions and methods used. The purchasers shall make their own tests to determine the suitability of such products for a particular purpose.

PROSOCO, Inc. warrants this product to be free from defects. **Where permitted by law, PROSOCO makes no other warranties with respect to this product, express or implied, including without limitation the implied warranties of merchantability or fitness for particular purpose.** The purchaser shall be responsible to make his own tests to determine the suitability of this product for his particular purpose. PROSOCO's liability shall be limited in all events to supplying sufficient product to re-treat the specific areas to which defective product has been applied. Acceptance and use of this product absolves PROSOCO from any other liability, from whatever source, including liability for incidental, consequential or resultant damages whether due to breach of warranty, negligence or strict liability. This warranty may not be modified or extended by representatives of PROSOCO, its distributors or dealers.

### CUSTOMER CARE

Factory personnel are available for product, environment and job-safety assistance with no obligation. Call 800-255-4255 and ask for Customer Care – technical support.

Factory-trained representatives are established in principal cities throughout the continental United States. Call Customer Care at 800-255-4255, or visit our website at [www.prosoco.com](http://www.prosoco.com), for the name of the PROSOCO representative in your area.

### BEST PRACTICES

Surfaces to be treated must be clean, dry and absorbent. Remove all loose construction debris and foreign materials. Remove all curing compounds, coatings, paint, wax, embedded soiling, rust, grease and oil using the appropriate PROSOCO surface preparation cleaner.

Remove all loose construction debris and foreign materials from surfaces to be treated using a dry broom. Remove all curing compounds, coatings, paint, wax, embedded soiling, rust, grease and oil using the appropriate PROSOCO surface preparation cleaner.

Acid-stained concrete must be thoroughly neutralized and rinsed prior to application.

Concrete floors may be treated with Consolideck® LS® or LS/CS® prior to application of SL100 Water Repellent.

Do not apply over Consolideck® LSGuard®.

Protect surfaces from rain, foot and vehicular traffic for at least 4 hours after treatment.

Clean tools and equipment immediately with mineral spirits or equivalent cleaning solvent. Remove rundown and spills as quickly as possible.

For treated concrete floors, use Consolideck® DailyKlean or LSKlean for maintenance cleaning. LSKlean contains lithium-silicate for improving surface density and preserving the surface sheen.

For treated concrete floors regularly maintained with auto scrubbers, see Consolideck® DailyKlean ULTRA 15 or DailyKlean ULTRA 30 for easy dilution. The same ease of dilution is available for deep cleaning with Consolideck® LSKlean ULTRA 15 and LSKlean ULTRA 30.

Never go it alone. If you have problems or questions, contact your local PROSOCO distributor or field representative. Or call PROSOCO technical Customer Care at 800-255-4255.