

GACOFLEX® LM-60AR LIQUID APPLIED URETHANE RUBBER MEMBRANE

DESCRIPTION

GacoFlex LM-60AR is a 100% solids liquid applied two component coating that cures into a water resistant polyurethane elastomeric membrane.

LM-60HAR is designed for application on horizontal and low slope surfaces, at the rate of at least four gallons per 100 ft² (15.14 L / 9.3 m²), to yield a 1/16" (1.6 mm) thick membrane. LM-60VAR is designed for the same application rate and yield on vertical surfaces.

RECOMMENDED USES

Intended primarily for use as a high build waterproofing membrane over concrete, metal and plywood.

This grade of LM-60 can be used in areas with a pH ≥ 4.

PRODUCT DATA

PROPERTY	VALUE		
Color	Black		
Consistency	LM-60HAR & LM-60VAR are thixotropic. LM-60HAR ranges between 25,000 to 40,000 centipoises at 75 °F (24 °C). LM-60VAR ranges between 100,000 to 160,000 centipoises at 75 °F (24 °C).		
Weatherability	GacoFlex LM-60AR has excellent durability up to 150 °F (82 °C). LM-60AR must be top coated. LM-60AR will crack and become brittle in exterior applications if not protected.		
Chemical Resistance	Excellent resistance to water immersion, good salt and alkali resistance. Excellent hydrolytic stability up to 150 °F (66 °C).		
Tensile	ASTM D412	Strength Elongation Permanent Set at Break	175 ± 10 psi (12 kg/m ²) 300% ± 20 10% max
Hardness	ASTM D2240	Shore A	30 min @ 70 °F (21 °C)
Adhesion	ASTM C836	Peel Strength	11 lb/inch (avg)
Tear Resistance	ASTM D624 Die C	lb/in min.	30 (5.4 kg(f) / cm)
Water Absorption	ASTM D471	21 days R.T.	1% max
Water Vapor Permeability	ASTM E96 Procedure BW	100 RH Difference	0.012 perm inches
Low Temperature Brittleness	ASTM D746	---	Pass @ -50 °F (-45 °C)

PACKAGED PRODUCT DATA

PROPERTY	VALUE
Packaging	1 gallon and 5 gallon metal containers
Applied Coverage	Mil ft ² per Gallon: 1600 (39.2 m ² / L / .02 mm) Applied Coverage: 4 Gals./100 ft ² . (15.14 L / 9.3 m ²) to yield 1/16" (1.6 mm) thickness
Solids	Volume: 100%
V.O.C.	N/A
Toxicity	GacoFlex LM-60AR Part B is an isocyanate prepolymer. When mixed with the polyol side (Part A) use adequate ventilation, avoid breathing vapors or spray mist and prolonged or repeated contact with skin. When spraying use a particulate matter mask, an approved organic matter cartridge respirator or fresh air mask.
Flash Point	ASTM D56 (Closed Cup) Above 200 °F (93 °C)
Adhesion	Excellent adhesion to clean, dry, plywood and concrete. Primers may be required for other surfaces. See below for specific primer.
Storage Stability	12 months @ 50 to 80 °F (10 to 27 °C)

APPLICATION

PROPERTY	VALUE
Primer	Metals GacoFlex E-5320 Plywood GacoFlex E-5691 Galvanized Steel GacoFlex E-5320 Concrete GacoFlex E-5691
Mixing Instructions	Stir the polyol side (Part A) to suspend any settled pigment. Completely empty the iso (Part B) container into the polyol side (Part A) and power mix for five minutes, scraping the pail side several times. Use a power mixer that will thoroughly agitate the mix (electric or compressed air powered). A Jiffy Mixer PS21 has been found to work well with LM-60HAR or LM-60VAR. Combine fifteen volumes of polyol (Part A) with one volume of iso (Part B) for quantities less than four gallons. Power mixing is mandatory for quantities over two gallons. Extreme care is required to mix in materials on the side and bottom of the mixing container.
Pot Life	One hour at 70 to 80 °F (21 to 27 °C). Can be extended to three hours by thinning with T-5112 (up to 10%).
Application	For best results, prime concrete surfaces with E-5691. Use a 5/16" x 5/16" V notched trowel or notched squeegee for application to 60 mil (1.52 mm) thickness. LM-60HAR is self-leveling on horizontal surfaces. LM-60VAR must be flat troweled to a smooth finish since it will not self-level. Contact Gaco for spray application information. Refer to specification for protection course or covering requirements. Use caution when backfilling or covering to avoid damage to the polyurethane membrane. WARNING – LM-60AR in direct contact with aged or new SBS and EPDM sheet membranes could cause their swelling and deterioration through time due to the strong solvency of the process oil in LM-60AR.

For specific Safety and Health information please refer to the Safety Data Sheet (SDS).

