

Vulkem[®] 350/346/346

Elastomeric, Waterproof Traffic Deck Coating System

Product Description

Vulkem[®] 350/346/346 is a modified polyurethane traffic deck coating system composed of a base coat (350), heavy duty intermediate coat (346) and a top coat (346). This unique waterproofing system is designed to have tenacious adhesion, extreme impact and abrasion resistance along with remarkable chemical stability. The elastomeric properties of the system's components enable the complete assembly to give and work with the concrete slab, bridging the shrinkage cracks.

Vulkem 350 Base Coat is a single-component urethane membrane that bonds firmly to clean, dry concrete and metal. It retains its integrity even if substrate movement causes hair-line cracks of up to 1/16" (1.5 mm). If cut or damaged, Vulkem 350 will prevent water migration between itself and the substrate. Vulkem 350 is available in roller (R) and in self-leveling (SL) grade for vertical and horizontal application.

Vulkem 346 Intermediate Coat is an aliphatic one-component urethane that is applied after the Vulkem 350 Base Coat has cured. The intermediate coat is loaded with aggregate to give the system excellent impact, abrasion and chemical resistance.

Vulkem 346 Top Coat is an aliphatic one-component polyurethane that is applied after the Vulkem 346 intermediate coat has cured. Interlaminary adhesion to Vulkem 346 is exceedingly strong. The top coat affords excellent abrasion resistance, UV stability and chemical resistance to complete this Vulkem Traffic Deck Coating System.

Basic Uses

Vulkem 350/346/346 is a cold-applied traffic deck coating system designed for waterproofing concrete slabs and protecting occupied areas underneath from water damage. Additionally, the system will protect the concrete from the damaging effects of water, deicing salts, chemicals, gasoline, oils and anti-freeze.

Features and Benefits

- Fast cure through time allows for use 72 hr after installation
- Mildew and fungus resistance safeguard concrete surfaces against environmental contaminants.
- Excellent durability and UV resistance extends the useful life of vehicular systems.
- Recoatable and compatible with other Tremco sealants and expansion joints, which enhance waterproofing protection with full system compatibility.

Availability

Immediately available from your local Tremco Sales Representative, Tremco Distributor or Tremco Warehouse.

Packaging

Vulkem 350: 5-gal (18.9-L) pails, 55-gal (208.2-L) drums.

Vulkem 346: 5-gal (18.9-L) pails, 55-gal (208-L) drums.

Colors

Vulkem 346 is available in Gray, Limestone and Slate Gray. Made-to-order and special colors are also available upon request.

SEALANT. WATERPROOFING MINIMUTE & RESTORATION INSTITUTE				
Issued to: Tremco Incorporated Product: Vulkem [®] 350 SL Basecoat & 346 Topcoat				
ASTM D 412: Tensile Strength of Top Coat				
Vulkem [®] 346 Tensile Strength: 2,831 psi; Elongation: 138%	Pass 🖌			
ASTM D 4541: Adhesion of Base Coa Vulkem® 350 SL Pull-off Adhesion: 284 psi	at Pass 🖌			
ASTM D 4060: Abrasion Resistance of Vulkem® 346 Abrasion Resistance: 36 mg loss – mg loss/1,000 cycles	of Top Coat Pass 🖌			
Validation Date: 4/13/17 - 4/12/22	2			
No. 0417-VBT0422	Copyright © 2017			
DECK COATING VALIDATION www.swrionline.org				

Installation

Concrete shall be water-cured and attain a 4000-psi minimum compressive strength. Concrete finish shall be a light steel trowel followed by a fine-hair broom, or equivalent ICRI #2-#4 finish. Moisture content in the concrete must be lower than 4.5% as measured by a Tramex CME 4 Moisture Meter. Depending on concrete construction and job site location, additional concrete testing may be required. Please contact your local Tremco Sales or Technical Representative.

Please refer to the Vulkem 350/346/346 Application Instructions for complete application details. The techniques involved may require modification to adjust to the jobsite conditions. Consult your Tremco Sales Representative or Tremco Technical Service for site conditions and requirements.

Applicable Standards

Conforms to:

ASTM C957

UL 790 – Class A Rating for non-combustible substrates

CSA S413-14 Limitations

- Do not apply to damp or contaminated surfaces.
- Use with adequate ventilation

Vulkem® 350/346/346

Elastomeric, Waterproof Traffic Deck Coating System

Warranty

Tremco warrants its Products to be free of defects in materials but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Tremco makes no other warranty, expressed or implied, including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE, with respect to Tremco Products. Tremco's sole obligation shall be, at its option, to replace or to refund the purchase price of the quantity of Tremco Product proven to be defective, and Tremco shall not be liable for any loss or damage.

Please refer to our website at <u>www.tremcosealants.com</u> for the most up-to-date Product Data Sheets.

NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.

TYPICAL PHYSICAL PROPERTIES

PROPERTY	TEST METHOD	VULKEM 350	VULKEM 346	VULKEM 346
Flash Point	Set-A-Flash	112°F (44.4°C)	85°F (29°C)	85°F (29°C)
% Solids	ASTM D1353	79%	72%	72%
Drying time @ 75F, 50% RH	ASTM D1640	25 mil film, 12 hr	10-12 mil film, 6 to 8 hr	10-12 mil film, 6 to 8 hr
Open to vehicular traffic		N/A	72 hr after cure	72 hr after cure
Weathering	ASTM D822	N/A	No effect	No effect
Salt Spray	ASTM B117	N/A	No effect	No effect
Viscosity	Brookfield C&P	8000 to 10000 cps	2000 to 3000 cps	2000 to 3000 cps
Elongation	ASTM D412	1040%	120%	120%
Tensile Strength	ASTM D412	320 psi	2800 psi	2800 psi
Hardness (Shore A)	ASTM D2240	60	85 to 95	85 to 95
Adhesion (Peel Strength)	ASTM D903	Unprimed concrete, 30 pli, 100% cohesive	100% cohesive failure	100% cohesive failure
Adhesion (Pull-Off)	ASTM D4541	280 psi	N/A	N/A
Abrasion Resistance (1000 cycles)	ASTM D4060	N/A	50 mg	50 mg
Accelerated Aging	ASTM D573	No loss of elongation or tensile strength	No loss of elongation or tensile strength	No loss of elongation or tensile strength

*Accelerated aging test. 1 daily cycle of UV and water spray greatly exceeds 1 day of real world exposure. Contact Tremco Technical Service or your local sales representative for more information.

1120/350346346-DS-DC

Please refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.

3735 Green Rd Beachwood OH 44122 216.292.5000 / 800.321.7906 1451 Jacobson Ave Ashland OH 44805 419.289.2050 / 800.321.6357

Tremco Commercial Sealants & Waterproofing 220 Wicksteed Ave Toronto ON M4H1G7 416.421.3300 / 800.363.3213

1445 Rue de Coulomb Boucherville QC J4B 7L8 514.521.9555

www.tremcosealants.com

