



**THE DOW CHEMICAL COMPANY
SALES SPECIFICATION**

Date Printed: 2022-01-04

Effective Date: 2020-06-05

Supersedes Date: 2020-06-04

Name: DOWSIL™ 756 SMS Building Sealant Adobe Tan

Specification Number: 000000862294

Shelf Life				
Container Type	Conditions of Handling	Conditions of Storage	Shelf Life	Deterioration Characteristics
All Approved Packaging		Store BELOW 32C/90F	360 Days	

Final Testing Requirements				
Test and Test Condition	Limit	Unit	Method	Note
Appearance, uniform viscous paste	Pass		CTM0176	
Tack free time	240 Max	min	CTM0095	
Extrusion rate	75 Min	g/min	CTM0364	
Specific Gravity, RT/50% RH	1.365 — 1.445		CTM0097	
Durometer, 7d/RT	20 — 45	ShoreA	CTM0099	
Modulus 50%, 7d/RT	20 — 60	psi	CTM0137A	

External Notes

- Dow Chemical warrants that the above designated material conforms to the listed sales specifications even though there may be no value reported.

Test Item	Limits
Durometer (7d/RT)	20 - 45 Shore A
Modulus 50% (7d/RT)	20 - 60 psi

READ PRECAUTIONARY INFORMATION AND MATERIAL SAFETY SHEETS. THIS PRODUCT IS SHIPPED IN COMPLIANCE WITH APPLICABLE LAWS AND REGULATIONS REGARDING CLASSIFICATION, PACKAGING, SHIPPING AND LABELING.

**THE DOW CHEMICAL COMPANY
SALES SPECIFICATION**

Name: DOWSIL™ 756 SMS Building Sealant Adobe Tan
Specification Number: 000000862294
Effective Date: 2020-06-05