



westcoat[®]
SPECIALTY COATING SYSTEMS

**PRODUCT
SPECIFICATION**

WP

WATERPROOF
RELIABLE MOISTURE BARRIERS

WP-81 & WP-82 Cement Modifiers

Description

WP-81 & WP-82 Cement Modifiers are high solids acrylic-polymer modifiers that will give increased strength, flexibility and adhesion to most cement based products. WP-81 & WP-82 make cement products more waterproof, more stain resistant and will extend the life of cement products, especially if exposed to the elements. WP-82 is the low odor version and otherwise equal to WP-81.

Uses

WP-81 & WP-82 are primarily used as an additive to Westcoat cement products so that they can be used to waterproof decks, resurface or patch concrete and for a variety of exterior decorative concrete treatments. WP-82 is mainly used on interior applications where low odor is desirable.

Advantages

Increases Strength and PSI • Allows Good Working Time • Allows Cement Products to be Feathered
• Increases Adhesion to Most Surfaces • Helps to Waterproof and Increase Water Resistance • Safe Water-Based, No Solvents • Increases Flexibility as More WP-81 or WP-82 is Added • WP-81 is ICC Evaluated ESR-2201 • WP-82 is Low Odor

Product Data			
Packaging	1 gal cans & 5 gal pails	Color	Milky White, dries clear
Coverages	~Varies depending on usage (see System Specification Sheets for desired system for coverage rates)	Mix Ratio	Varies depending on usage (see System Specification Sheets for mix ratios)
VOC Content	Zero VOC	Shelf Life	2 years in unopened packaging

Inspection

Surface must be clean, dry and free of grease, paint, oil, dust or curing agents. It should have a rough finish, be porous and feel like 30 to 50 grit sandpaper.

Preparation

Prepare concrete surface by sanding, grinding, scarifying, waterblasting, sandblasting or shot blasting to achieve a clean, porous and uniform surface that will allow product to soak in and bond permanently. When coating over plywood, surface must be clean, dry and free of all debris. See System Specification Sheets for complete preparation directions. Note: The most common reason for coating failure is due to lack of preparation.

DISCLAIMER: PURCHASER'S SOLE AND EXCLUSIVE REMEDY AGAINST THE MANUFACTURER OF WESTCOAT, SHALL BE LIMITED SOLELY TO THE REPLACEMENT OF ANY DEFECTIVE MATERIAL OR A PAYMENT BY THE MANUFACTURER IN AN AMOUNT EQUAL TO THE COST OF THE ORIGINAL MATERIAL.



4007 Lockridge St • San Diego, CA 92102
800-250-4519 • Fax 619-255-7187 • westcoat.com

1 of 3
WP-81 & WP-82 12/19



westcoat[®]
SPECIALTY COATING SYSTEMS

**PRODUCT
SPECIFICATION**

WP

WATERPROOF
RELIABLE MOISTURE BARRIERS

WP-81 & WP-82 Cement Modifiers

Mixing

Stir prior to use. Typically combine 1 to 1¼ gallons per 50 lbs. bag of cement for most Westcoat applications. For complete mixing and application instructions, see System Specification Sheets.

Thinning

For use as a primer, thin with 4 parts water to 1 part WP-81 or WP-82.

Coverage

Will vary depending on use.

Applying Product

For Small Patches - Cut or chip open cracks or voids and clean. Mix one gallon of WP-81 or WP-82 with 1 bag of Westcoat Cement such as TC -1, 2, 3, 4 or 5. Combine the WP-81 or WP-82 and cement and add water to desired consistency. Mix thoroughly with a low rpm drill motor. Place the material into the area to be patched and smoothed or finished to desired effect using a trowel or float. (For larger patches see Concrete Patch System Specification Sheet).

As a Stucco Additive - WP-81 or WP-82 is an excellent additive to most stucco products. The stucco will bond better, weather better with reduced cracking and be more waterproof. When adding to stucco, simply mix 1-2 quarts of WP-81 or WP-82 per 90lb. bag of stucco. Add water to achieve desired consistency. Mix thoroughly with a low rpm drill motor. WP-81 or WP-82 will make the stucco a bit stickier and will cause it to cure more rapidly.

Freshen up Concrete - Combine ½ gallon of WP-81 or WP-82 and up to 1 gallon of water with 1 bag of TC-5 Grout Texture Cement to achieve the desired consistency. See complete Texture-Crete Broom On System Specification Sheet.

As a Decorative or Waterproof Coating - Combine the WP-81 or WP-82 as described in the System Specification sheets for the Westcoat ALX™ waterproof decking system and Texture-Crete® concrete resurfacing system. See ALX™ and Texture-Crete® System Specification Sheets for complete instructions.

Dry Time

Allow 4 to 6 hours drying time (depending on temperature and application) before permitting light pedestrian traffic. For best results, allow to cure 24 hours before direct traffic is permitted or additional coats are applied. Allow 48 hours before heavy objects are placed on the surface.

Clean Up

Uncured material should be removed with soap and warm water. Cured material should be removed mechanically or with an environmentally-safe solvent.


DISCLAIMER: PURCHASER'S SOLE AND EXCLUSIVE REMEDY AGAINST THE MANUFACTURER OF WESTCOAT, SHALL BE LIMITED SOLELY TO THE REPLACEMENT OF ANY DEFECTIVE MATERIAL OR A PAYMENT BY THE MANUFACTURER IN AN AMOUNT EQUAL TO THE COST OF THE ORIGINAL MATERIAL.



westcoat[®]

4007 Lockridge St • San Diego, CA 92102
800-250-4519 • Fax 619-255-7187 • westcoat.com

2 of 3
WP-81 & WP-82 12/19



WP-81 & WP-82 Cement Modifiers

Limitations

- Please read the manufacturer’s complete System Specification Sheet before beginning your project.
- Do not use WP-81 or WP-82 if the temperature is below 55°F or above 95°F.
- Rain will wash away uncured Westcoat acrylic products.
- If inclement weather threatens, cover deck to protect new application.
- Do not allow any Westcoat products to freeze.

Health Precautions

Inhalation of vapor or mist can cause headache, nausea, irritation of nose, throat and lungs. Prolonged or repeated skin contact can cause slight skin irritation.

Emergency and First Aid Procedures – If inhalation occurs, remove victim to fresh air and give artificial respiration if subject is not breathing. If product is ingested, induce vomiting if victim is conscious. Wash skin with soap and water if contact to skin causes irritation. Flush eyes with water if product contact occurs. Contact physician immediately for any health emergencies.

Technical Data

Technical Data	WP-81 & WP-82 Cement Modifier
Type	100% Acrylic
Solids Content	47% by weight
60% Gloss (4 mil. dry film)	85
Viscosity	150cps
Flash Point	>200°F (TCC)
Maximum VOC	0 grams per liter

DISCLAIMER: PURCHASER’S SOLE AND EXCLUSIVE REMEDY AGAINST THE MANUFACTURER OF WESTCOAT, SHALL BE LIMITED SOLELY TO THE REPLACEMENT OF ANY DEFECTIVE MATERIAL OR A PAYMENT BY THE MANUFACTURER IN AN AMOUNT EQUAL TO THE COST OF THE ORIGINAL MATERIAL.