



**THE DOW CHEMICAL COMPANY  
SALES SPECIFICATION**

**Date Printed:** 2022-01-04

**Effective Date:** 2018-10-31

**Supersedes Date:** 2018-10-31

**Name:** DOWSIL™ 795 Silicone Building Sealant White

**Specification Number:** 000000839104

**Shelf Life**

<b>Container Type</b>	<b>Conditions of Handling</b>	<b>Conditions of Storage</b>	<b>Shelf Life</b>	<b>Deterioration Characteristics</b>
All Approved Packaging	Refrigerate > 7 days	Store BELOW 27C/81F	360 Days	

**Final Testing Requirements**

<b>Test and Test Condition</b>	<b>Limit</b>	<b>Unit</b>	<b>Method</b>	<b>Note</b>
Appearance, uniform viscous paste	Pass		CTM0176	
Tack free time	180 Max	min	CTM0095	
Extrusion rate	75 Min	g/min	CTM0364	
Flow	0.2 Max	inch	CTM0062	
<b>Test Frequency:</b>	audit once per year			
Durometer, 7d/RT	25 Min	ShoreA	CTM0099	
Tensile, 7d/RT	125 Min	psi	CTM0137A	
Elongation, 7d/RT	450 Min	%	CTM0137A	
Tear Die B, 7d/RT	20 Min	lb/in	CTM0159A	

**THE DOW CHEMICAL COMPANY**  
**SALES SPECIFICATION**

**Name:** DOWSIL™ 795 Silicone Building Sealant White  
**Specification Number:** 000000839104  
**Effective Date:** 2018-10-31

**External Notes**

---

- 1 Dow Chemical warrants that the above designated material conforms to the listed sales specifications even though there may be no value reported.

Test Item	Limits
Flow	< = 0.2 inches
Durometer (7d/RT)	> = 25 Shore A
Tensile (7d/RT)	> = 125 psi
Elongation (7d/RT)	> = 450 %
Tear (7d/RT)	> = 20 lb/inch

READ PRECAUTIONARY INFORMATION AND MATERIAL SAFETY SHEETS. THIS PRODUCT IS SHIPPED IN COMPLIANCE WITH APPLICABLE LAWS AND REGULATIONS REGARDING CLASSIFICATION, PACKAGING, SHIPPING AND LABELING.