



EUCLID CHEMICAL

TAMMS H/P PRIMER

PRIMER FOR CONCRETE OR MASONRY SURFACES

DESCRIPTION

TAMMS H/P PRIMER aids in the proper curing of acrylic resin or cement-based masonry coatings, especially when applied to hot or porous surfaces. TAMMS H/P PRIMER dries rapidly to create a breathable barrier within the substrate surface. The barrier retards the excessive absorption of moisture from the coating into the substrate, and aids in the proper curing of the coating. This action helps to minimize “cratering” of acrylic coatings, and the formation of shrinkage cracks in cementitious materials. TAMMS H/P PRIMER is necessary on porous surfaces or when the weather is warm and windy.

PRIMARY APPLICATIONS

- Exterior/interior, above/below grade
- Concrete and masonry surfaces
- Brick
- Stone
- Concrete block surfaces such as split face, textured, regular, or lightweight block
- Precast, textured, lightweight and formed concrete

FEATURES/BENEFITS

- Provides a stable base for Euclid Chemical coatings
- Aids in achieving appropriate coverage rates for subsequent coatings

TECHNICAL INFORMATION

TAMMS H/P PRIMER is a milky white emulsion of 100% acrylic polymer solids and modifiers in a water-based formulation. TAMMS H/P PRIMER turns clear with a slight gloss when dry.

PACKAGING

TAMMS H/P PRIMER is packaged in 5 gal (18.9 L) pails and 55 gal (208 L) drums.

SHELF LIFE

2 years in original, unopened container

COVERAGE

The coverage rates below are approximate and for estimating purposes only. Actual surface texture and porosity will determine the total amount of TAMMS H/P PRIMER required.

	ft ² /gal	m ² /L
Porous	100 to 150	(2.5 to 3.7)
Non Porous	200 to 300	(4.9 to 7.3)

DIRECTIONS FOR USE

Surface must be structurally sound, clean, dry, and free of contaminants. Repair surface defects, cracks, and voids before applying TAMMS H/P PRIMER. Cure new concrete and masonry surfaces minimum 28 days. Provide an absorptive surface on all substrates, including smooth precast or formed concrete by abrading the surface. Apply TAMMS H/P PRIMER to a dry surface, and do not apply when rain is expected within 4 hours or if the primed surface cannot be topcoated within 24 hours.

Mixing: Stir TAMMS H/P PRIMER slowly and thoroughly, using slow speed mixing equipment that will not aerate the product. Do not dilute TAMMS H/P PRIMER.

Application: Use airless spray equipment with 0.017 to 0.021 inch (0.43 to 0.53 mm) orifice size spray tips to apply TAMMS H/P PRIMER. Hold spray gun 12 to 18 inches (30.4 to 45.7 cm) from the wall surface, and apply using a “cross coat” technique consisting of a horizontal pass followed by a vertical pass. For hand application, use equipment designed for latex paints, and dampen the brushes or the 1½ inch (3.8 cm) nap rollers with water before use. Thoroughly wet the surface with TAMMS H/P PRIMER to the point of saturation with no run down. Pick up any drips or runs with a brush or roller.

TAMMS H/P PRIMER is rapid drying, and the finish coat may be applied as the primer dries, but no later than 24 hours after primer application. Labor costs on large projects may be reduced by using separate application systems to apply the TAMMS H/P PRIMER and the finish coat during the same “drop”.

CLEAN-UP

Clean tools and application equipment immediately after use with detergent and hot water. Clean overspray or drips, while still wet, with detergent and hot water. Clean glass and metal surfaces before material dries. Dried material will require strong solvents or abrasion for removal.

PRECAUTIONS/LIMITATIONS

- Do not thin or dilute TAMMS H/P PRIMER.
- Do not apply to external surfaces if rain is forecast within 4 hours.
- Do not apply TAMMS H/P PRIMER below 50°F (10°C) or above 90°F (32°C), or over frozen or frost-filled surfaces.
- Do not apply TAMMS H/P PRIMER to non-absorbent materials such as glass, metal, glazed brick, or glazed tile. Primer should be topcoated within 24 hours after application.
- Store at temperatures between 50°F to 90°F (10°C to 32°C).
- Protect from freezing. If material was ever frozen, do not use.
- In all cases, consult the Safety Data Sheet before use.

Rev. 01.19

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.