



LIFE PAINT

PRODUCT SPECIFICATIONS



WATERPROOFING

LIFE DECK SEAL GUARD

Description

Life Deck Seal Guard is a 30 or 40 mil. thick rubberized asphalt, self-sealing, self-adhering waterproof membrane reinforced with a non-woven polyester fabric. Seal Guard has a white polyester scrim, which allows light foot traffic and a short period of UV exposure.

Uses

Life Deck Seal Guard is primarily used as a secondary waterproofing membrane in critical situations under the AL UT system or any areas where a self-sealing, self-adhering waterproof membrane is needed.

Advantages

- *Self-sealing
- *Self-adhering
- *Economical
- *Reinforced
- *User Friendly
- *Withstands Light Foot Traffic
- *Short UV Protection

Packaging

6" x 100' 30 mil
12"x 100' 30 mil
36"x 67' 40 mil

Inspection/Surface Preparation

Be sure the surface is clean, dry and free of grease, paint, oil, dust or any foreign material that may prevent proper adhesion. All nails and screws must be flush with the surface.

Application

One method of application is to roll out the membrane with the white side up and measure individual lengths with 2" minimum overlap. Pull the material tight from each end and remove the 2-1/2" strip of the overlap release film and adhere to the deck.

Another method is to pull 12" to 24" of the release film and position the roll where desired. Adhere the membrane firmly onto the deck. Begin pulling the release film in the opposite direction. The roll will follow as the release film is removed. Smooth the membrane as the adhesive back comes into contact with the deck.

Install Life Deck Seal Guard under and/or over flashing to help seal nail holes. Because the material is not UV stable, the material is to be held back from the edge of the flashing and covered by the coating to be installed.

Limitations

- *Do not leave exposed to UV for more than 2 weeks.
- *Do not install in temperatures above 90°F or below 40°F.
- *Do not store rolls on end.

WARRANTY: When the warranted product is applied in accordance with label instructions and common sense widely accepted painting practice and procedures, Life Paint will warrant said product against manufacturing defects that might cause premature failure such as blistering, peeling, or unusual wear. Directions are as complete as possible but cannot encompass all conditions, applications, and/or surfaces beyond manufacturer's control. In the event of a warranted failure and upon the presentation of proof of purchase, the remedy will be the provision price for said product. This warranty does not include labor or the costs associated with labor. This warranty may not be transferred or assigned and extends specific legal rights which may vary from state-to-state. No other warrantee is expressed or implied.

Technical Data

Thickness
Tensile Strength-reinforcing only (ASTM D882-A)
Elongation, ultimate failure of SBS mass (ASTM D412)
Pliability

30-40 mils. +- 5
1400 psi
500%min.
Pass