



TAMMSFLEX NS, TAMMSFLEX SL

TWO-PART POLYSULFIDE JOINT SEALANTS

EUCLID CHEMICAL

DESCRIPTION

TAMMSFLEX sealants are two-part, elastomeric, polysulfide caulking and sealing compounds. TAMMSFLEX cures at normal temperatures creating a tough elastomeric seal that adheres tenaciously to masonry, concrete, metal and wood. TAMMSFLEX will withstand repeated expansion and contraction and remain resilient through daily and seasonal cyclic changes in temperature. TAMMSFLEX has excellent chemical, solvent, and water resistance and will withstand joint movement of up to $\pm 25\%$.

PRIMARY APPLICATIONS

TAMMSFLEX NS is a non-sag gun grade sealant designed for use in vertical and non-traffic bearing horizontal joints subject to expansion resulting from temperature changes. TAMMSFLEX NS is used for all normal construction joints such as panel and curtain wall construction, copings, masonry joints, bridge abutments and building joints. TAMMSFLEX NS is formulated for use in joints subject to long term contact with water and may be used in water reservoirs, dams and foundation joints.

TAMMSFLEX SL is a flowable, self-leveling, traffic grade sealant designed for horizontal joints in patios, plazas, floors, sidewalks, roadways and other areas exposed to pedestrian or vehicular traffic.

FEATURES/BENEFITS

- Joint sealant between similar/dissimilar materials
- Glazing & caulking
- Resistant to splash & spill contact with jet fuel
- Perfect for dynamic joints subjected to chemicals
- Service temperatures from -50°F to 190°F (-45°C to 87°C)

TECHNICAL INFORMATION

Typical Engineering Data

The following are typical values obtained under laboratory conditions. Expect reasonable variation under field conditions.

Specific gravity mixed	1.6
% Solids	100
% Joint movement	± 25
Hardness, Shore A (ASTM D2240)	25 to 30
Pot life	approx 2 hrs
Tack free	12 to 24 hrs
% Elongation (ASTM D638)	500 to 550

Tensile strength (ASTM D638) psi (MPa) 150 to 200 (3.68 to 4.91)
100% Modulus psi (MPa)	50 (1.23)
200% Modulus psi (MPa)	80 (1.96)
Chemical Resistance	see full chemical resistance chart at euclidchemical.com
Appearance: TAMMSFLEX is gray/brown in color.	

PACKAGING

TAMMSFLEX NS and TAMMSFLEX SL are packaged in 1.5 gal (5.68 L) units. TAMMSFLEX PRIMER is a two-part product; Part A and Part B are each packaged in 1 qt (0.95 L) containers.

SHELF LIFE

18 months in original, unopened containers

SPECIFICATIONS/COMPLIANCES

TAMMSFLEX NS: ASTM C920, Type M, Grade NS, Class 25, Use NT, M, G, A, and O

TAMMSFLEX SL: ASTM C920, Type M, Grade P, Class 25, Use NT, M, G, A, and O

IAPMO/ANSI Standard 61 (TAMMSFLEX NS)

COVERAGE

Inches (cm)		Linear ft/gal (m/L)
Joint Width	Joint Depth	
1/4 (0.64)	1/4 (0.64)	308 (25)
3/8 (0.95)	3/8 (0.95)	102 (8)
1/2 (1.27)	1/2 (1.27)	77 (6.2)
5/8 (1.6)	1/2 (1.27)	61 (4.9)
3/4 (1.9)	1/2 (1.27)	51 (4.1)
7/8 (2.2)	1/2 (1.27)	44 (3.5)
1 (2.5)	1/2 (1.27)	38 (3.1)

Note: TAMMSFLEX coverage rates are approximate and provided for estimating purposes only.

DIRECTIONS FOR USE

Surface Preparation: Cure new concrete or masonry surfaces for 28 days. Surface of the joint must be clean, sound, and dry. Contaminants such as previously applied sealants, form release agents, grease, oil, etc. must be removed by scarifying, wire brushing, or sanding. All traces of asphalt or other bituminous materials must be removed. Dust should be blown out of the joint with oil free, moisture free compressed air. Protective coatings of lacquer or oil must be removed from metal surfaces with MEK or xylene. Do not apply TAMMSFLEX if the temperature of the sealant, air, or substrate is below 40°F (4°C).

Priming: Priming is not normally required with common building materials. A primer may be required for optimum adhesion in demanding environments, continuous immersion for example, or for certain substrates. In these cases TAMMSFLEX PRIMER should be used and the sealant must be applied within 8 hours after priming. See TAMMSFLEX PRIMER technical data sheet for full instructions on use. A field trial is recommended to determine actual adhesion with and without a primer.

Joint Design: The minimum width of the joint should be 4 times the anticipated movement but not less than 1/4" (0.64 cm). Maximum recommended joint width is 1" (2.5 cm). In joints up to 1/2" (1.3 cm) wide, the sealant depth should be equal to the joint width. In joints from 1/2" (1.3 cm) to 1.0" (2.5 cm) wide, sealant depth should be 1/2" (1.3 cm). In joints deeper than 1/2" (1.3 cm), a flexible, non-asphaltic or non-oil impregnated backing material should be used to fill the lower part of the joint cavity. For traffic bearing areas, a round rod of synthetic rubber of the same Shore A as TAMMSFLEX SL (or harder) is recommended. The backing rod should be round to minimize the stress on the joint sealant. The sealant should not adhere to the bottom of the joint or the backing material. A strip of polyethylene film may be installed as a bond breaker between the filler or the bottom of the joint and the sealant.

Mixing - TAMMSFLEX PRIMER: Mix Part A with Part B for 3 minutes. After application, allow the primer to cure for 2 hours before applying TAMMSFLEX NS or TAMMSFLEX SL. See TAMMSFLEX PRIMER technical data sheet for further information.

Mixing - TAMMSFLEX NS or SL: Thorough mixing of the components is essential for maximum performance of TAMMSFLEX. Remove the activator (Part B) from the base material (Part A) container. Also remove the polyethylene sheet or tray. Mix Part A with a slow speed 1/2" (1.3 cm) drill (250 to 300 rpm) with a "Jiffy" mixing paddle. Then add Part B to Part A and mix for 3 to 4 minutes until the material is completely blended with a uniform color. While mixing, periodically scrape down the sides of the container and mixing paddle.

Caution: Do not mix base and activator components from one shipment with components from another.

Application: TAMMSFLEX sealants allow 1 to 2 hours of working time under normal conditions. Do not mix more than can be applied in this period. TAMMSFLEX NS can be applied with standard caulking equipment. Always fill the joint from the bottom up or from the inside out to avoid entrapping air. The gun nozzle should be the largest size which can be inserted to the bottom of the joint. Tooling is recommended immediately after application to ensure full contact with the joint surfaces. Dry tooling is preferred. TAMMSFLEX SL may be poured into the joint, as it is self-leveling.

CLEAN-UP

Clean tools and equipment immediately after application with xylene or acetone. Clean up spills and drips while still wet with the same solvents.

PRECAUTIONS/LIMITATIONS

- Store at temperatures between 50°F to 90°F (10°C to 32°C).
- Protect from moisture.
- Do not mix base and activator components from one shipment with components from another.
- For water immersion conditions allow TAMMSFLEX to cure for 7 days at 70°F (21°C) prior to filling with water.
- Do not use TAMMSFLEX for submerged applications in swimming pools.
- In all cases, consult the Safety Data Sheet before use.

Rev. 05.20

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.