



e.spray



Product Description

Basic Use: e.spray is a key component to EPRO's redundant field installed composite design concept. e.spray is a polymer modified asphalt (PMA) applied to nominal dry thicknesses of 60, 80, and 100 mils depending on the E.Series system configuration. For robust horizontal deck applications, a 120 mil reinforced option should be specified. Spray applied to form a seamless barrier, e.spray is an integral component to all E.Series systems due to its ability to further enhance and bond to a variety of materials; these materials include, high density polyethylene (HDPE), polyolefin sheets, geotextile fabric, wood, metal, foam insulation, and concrete based surfaces (green concrete, shotcrete and concrete masonry units (CMU)). e.spray is applied with a proprietary self-contained sprayer designed to produce high build, monolithic, and rapidly curing membranes.

Composition: e.spray is a non-hazardous, low-viscosity, water-based, anionic asphalt emulsion modified with a blend of synthetic polymerized rubbers and proprietary additives. e.spray is highly stable during transit and proper storage, but becomes highly reactive during the spray application to form a rapidly cured membrane with exceptional bonding, elongation, and hydrophobic characteristics.

Benefits

- Provides a layer of seamless protection and redundancy in all E.Series system assemblies
- Hydrophobic and resistant to methane gas
- Non-toxic, non-hazardous, non-flammable, and VOC free
- Forms a tenacious bond directly to concrete
- Application to damp substrates is acceptable
- Can be applied in below freezing temperatures with proper equipment

Limitations

- Surfaces shall be free of dirt and debris
- Material should be stored above 40°F and not allowed to freeze
- Not a traffic bearing surface, additional protection required
- Must not be applied to ponded water
- Direct foot traffic should be limited when ambient air temperatures are greater than 100°F
- Green concrete may require a primer coat prior to application

Technical Data

Shelf life: 6 months. The ability to apply the product beyond its estimated shelf life is dependent on storage conditions and homogeneity of the product. Storing material in an enclosed temperature controlled environment that maintains a minimum ambient temperature of 65° Fahrenheit will likely extend the shelf life beyond 6 months.

Properties: See physical properties table

Specification Writer: Contact EPRO before writing specifications on this product. E.Series system assemblies should be reviewed in order to meet project specific site conditions.

Additional test information available upon request.

Installation

EPRO Authorized Applicators must be approved in writing by EPRO prior to receiving a contract in order to qualify for a warranty for this product and system assembly.

Surface Preparation: All surfaces shall be prepared in accordance to manufacturer's specifications. Surfaces shall be uniform, free of loose materials, and surface contaminants. Contaminant and loose debris shall be removed prior to application by suitable methods.

Application: Please refer to manufacturer's specifications. e.spray shall be spray applied to the specified nominal mil thickness. When properly applied, e.spray will set up immediately on the surface and promptly start the curing process. Light foot traffic is acceptable, but must be limited to the authorized EPRO applicator. The initial cure is complete when e.spray is no longer ejecting moisture, 12 to 48 hours depending on ambient air conditions.

Availability and Packaging

Contact EPRO sales representative for local distributors or authorized applicators (www.eproinc.com).

e.spray is available in the following packaging options:

55 gallon drum
275 gallon tote
330 gallon tote



e.spray

Warranty

Limited Warranty: EPRO Services, Inc. believes to the best of its knowledge that performance tables are accurate and reliable. EPRO warrants this product to be free from defects. EPRO makes no other warranties with respect to this product, express or implied, including without limitation the implied warranties of MERCHANTABILITY OR FITNESS FOR PARTICULAR PURPOSE. EPRO's liability shall be limited in all events to supplying sufficient product to retreat the specific areas to which defective product has been applied. EPRO shall have no other liability, including liability for incidental or resultant damages, whether due to breach of warranty or negligence. This warranty may not be modified or extended by representatives of EPRO or its distributors.

Equipment

Spray System: AD-55 Sprayer is available through EPRO. To discuss alternative spray machine options, please contact EPRO directly.

Smoke Testing: EPRO Smoke Test Machine for underslab applications

Technical Services and Information

Complete technical services and information are available by contacting EPRO at 800.882.1896 or www.eproinc.com.

This product was formally known as Ecoline-S.

Typical Physical Properties

Physical Property	Test Method	Value
Color		Brown to Black
Solvent Content		No Solvents
Shelf Life		6 months
Tensile Strength	ASTM 412	32 psi
Elongation	ASTM 412	4140%
Resistance to Decay	ASTM E 154 Section 13	4% Perm Loss
Accelerated Aging	ASTM G 23	No Effect
Moisture Vapor Transmission	ASTM E 96	0.026 g./sq. ft./hr.
Hydrostatic Water Pressure	ASTM D 751	26 psi
Perm Rating	ASTM E 96 (US Perms)	0.21
Methane Transmission Rate	ASTM D 1434	0
Adhesion to Concrete & Masonry	ASTM C 836 & C 704	11 lbf./inch
Adhesion to HDPE	ASTM C 836	28.363 lbf./inch
Adhesion to Polypropylene Fabric	ASTM C 836	31.19 lbf./inch
Hardness	ASTM C 836	80
Crack Bridging	ASTM C 836-00	No Cracking
Low Temp. Flexibility		No Cracking at -20° C

Packaging: 55 gallon drum, 275 gallon tote, 330 gallon tote