

30

Coatings for Concrete
and Masonry

MasterProtect[®] P 150

pH Recommendations for the Application of MasterProtect P 150

FORMERLY THORO[®] CM PRIMER

The purpose of this memo is to address our recommendations for the allowable pH of a substrate prior to the use of our MasterProtect P 150.

Typical recommendations for when MasterProtect P 150 can be applied to a concrete, masonry, or stucco substrate would include but not be limited to;

- The substrate moisture content should be below 12% when tested with a surface moisture meter.
- Concrete substrates should have reached 80% of its design strength.
- Surface pH of masonry or stucco should be at 12 pH or below.

Additional application recommendations can be found in the MasterProtect P 150 Technical Data Guide.

