

# ALSAN® RS

## 230 FLASH

ALSAN® RS 230 FLASH  
PRODUCT #

L-RS022SC (summer grade - pebble grey)  
L-RS024SC (summer grade - bright white)  
L-RS022WC (winter grade - pebble grey)  
L-RS024WC (winter grade - bright white)

## PRODUCT DATA SHEET

### DESCRIPTION & FEATURES

ALSAN RS 230 Flash is a high performance, rapid-setting, polymethyl methacrylate (PMMA) liquid resin for use in flashing applications. ALSAN RS 230 Flash is catalyzed with ALSAN RS catalyst powder and combined with ALSAN RS Fleece to form a flexible, monolithic, reinforced membrane.

### STORAGE

Always store closed containers in cool, ventilated and dry locations away from heat and oxidizing agents. Do not store in direct sunlight or in temperatures below 32°F (0°C) or above 77°F (25°C). Approximate shelf life is twelve months from date of shipment when properly stored, sealed and unmixed.

### APPLICATION

ALSAN RS 230 Flash is applied via brush or roller. Prior to application, refer to published specifications and approved details for complete application instructions. The applicator is responsible for ensuring conditions are appropriate to proceed with proper application methods.



APPLICATION



BRUSH



ROLLER

QUICK FACTS  
WINTER

UNIT SIZE (kg)	AMBIENT TEMP (°F)	SUBSTRATE TEMP (°F)	RESIN TEMP (°F)	POT LIFE (min)	RAIN PROOF (min)	NEXT LAYER (hour)	FULLY CURED (hour)
12.5 (9.8 L)	23-68 (-5 to 20°C)	23-68 (-5 to 20°C)	37-68 (3 to 20°C)	15-20 at 68°F (20°C)	45-60 at 68°F (20°C)	1-2 at 68°F (20°C)	5 at 68°F (20°C)

QUICK FACTS  
SUMMER

UNIT SIZE (kg)	AMBIENT TEMP (°F)	SUBSTRATE TEMP (°F)	RESIN TEMP (°F)	POT LIFE (min)	RAIN PROOF (min)	NEXT LAYER (hour)	FULLY CURED (hour)
12.5 (9.8 L)	50-95 (10 to 35°C)	50-122 (10 to 50°C)	50-86 (10 to 30°C)	15-20 at 68°F (20°C)	30-45 at 68°F (20°C)	1-1.5 at 68°F (20°C)	3-6 at 68°F (20°C)



**SOPREMA®**

[www.soprema.us](http://www.soprema.us)  
310 Quadral Drive, Wadsworth, Ohio 44281  
Toll Free: (800) 356-3521 | Tel: (330) 334-0066

TECHNICAL INFORMATION & TESTING

**APPROXIMATE COVERAGE RATES**

SUBSTRATE PROFILE	12.5 KG UNIT ft <sup>2</sup> (m <sup>2</sup> )	MINIMUM TOTAL CONSUMPTION kg/ft <sup>2</sup> (kg/m <sup>2</sup> )	BASE COMPONENT CONSUMPTION kg/ft <sup>2</sup> (kg/m <sup>2</sup> )	TOP COAT CONSUMPTION kg/ft <sup>2</sup> (kg/m <sup>2</sup> )	TOTAL THICKNESS mils(mm)	BASE COAT mils (mm)	TOP COAT mils (mm)
Smooth	42 (3.9)	<b>0.28 (3.0)</b>	0.18 (2.0)	0.10 (1.0)	<b>98 (2.5)</b>	63 (1.6)	35 (0.9)
Typical	40 (3.7)	<b>0.30 (3.3)</b>	0.20 (2.3)		<b>106 (2.7)</b>	71 (1.9)	
Granulated	34 (3.2)	<b>0.35 (3.8)</b>	0.25 (2.8)		<b>122 (3.1)</b>	87 (2.3)	
Rough	30 (2.8)	<b>0.40 (4.3)</b>	0.30 (3.3)		<b>140 (3.5)</b>	105 (2.7)	

Catalyst quality will range from 2-6% (by weight) dependent on the ambient temperature.

**CATALYST MIXING CHART**

CATALYST REQUIRED	SUMMER FORMULATION				WINTER FORMULATION					
	4% Catalyst 50°F (10°C) to 68°F (20°C)		2% Catalyst 68°F (20°C) to 95°F (35°C)		6% Catalyst 23°F (-5°C) to 37°F (3°C)		4% Catalyst 37°F (3°C) to 50°F (10°C)		2% Catalyst 50°F (10°C) to 68°F (20°C)	
12.5 kg can	<b>5</b> 0.1 kg packets		<b>2.5</b> 0.1 kg packets		<b>7</b> 0.1 kg packets		<b>5</b> 0.1 kg packets		<b>2.5</b> 0.1 kg packets	
1 kg	TBSP	kg	TBSP	kg	TBSP	kg	TBSP	kg	TBSP	kg
	4	0.04	2	0.02	6	0.06	4	0.04	2	0.02
1 liter (~1.2 kg)	5	0.05	2.5	0.024	7	0.07	5	0.05	2.5	0.024

**PHYSICAL PROPERTIES**

PROPERTY	MD	XMD	TEST METHOD
Peak load @ 73.4°F (23°C) control, lbf/in (kN/mm)	70 (12.3)	60 (10.5)	ASTM D5147
Elongation @ 73.4°F (23°C) control, %	55	70	ASTM D5147
Peak load @ 73.4°F (23°C) post heat aging, lbf/in (kN/mm)	70 (12.3)	70 (12.3)	ASTM D5147
Elongation @ 73.4°F (23°C) post heat aging, %	50	50	ASTM D5147
Peak load @ 73.4°F (23°C) post acc. weathering, lbf/in (kN/mm)	75 (13.1)	75 (13.1)	ASTM D5147
Elongation @ 73.4°F (23°C) post acc. weathering, %	55	55	ASTM D5147
Peak load @ 0°F (-18°C), lbf/in (kN/mm)	130 (22.8)	110 (19.3)	ASTM D5147
Elongation @ 0°F (-18°C), %	60	85	ASTM D5147
Tear resistance, lbf (N)	80 (356)	70 (311)	ASTM D5147
Dimensional stability, %	0.1	0	ASTM D5147
Static puncture resistance, lbf (N)	Pass 56 (249)		ASTM D5602
Shore A hardness, durometer	70		ASTM D2240
Water absorption, %	0.8		ASTM D570 (@ 212°F)
Water vapor permeance, perms	0.2		ASTM E96
Low temperature flexibility, °F (°C)	Pass -33 (-36.1)	Pass - 33 (-36.1)	ASTM D7264
Low temperature crack bridging	No cracks		ASTM C1305
Self-ignition, °F (°C)	752 (400)		ASTM D1929
Smoke density index	105		ASTM E84
Rate of burning, in/min (m/hr)	0.9 (1.4)		ASTM D635

CODES & APPROVALS

