



# LIFE PAINT

## PRODUCT SPECIFICATIONS



### WATERPROOFING

#### LD51 Hardener

#### Base Membrane Thickener

**Description:** LD51 Hardener is a single component, low viscosity, accelerating agent. This accelerator enhances the moisture curing characteristics of all grades of LD-246.

**Clean Up:** Equipment should be cleaned with an environmentally safe solvent, as permitted under local regulations, immediately after use.

#### Advantages

- \* Fast Cure Time
- \* Can Save Labor Costs (Faster Cure Times)

**Warranty:** No warranty is supplied with this product.

#### Packaging

1 Quart

#### Mixing Instructions:

LD51 Hardener may be mixed into the LD-246 surface protection coating by using a mechanical mixer. Mix LD51 into the topcoat until a homogeneous mixture and color is achieved. Do not mix in an up and down motion.

The mixing ratio of LD51 to base membrane is: 1/2 pint (or less) LD51 to 1 gallon base membrane (0.24 liters LD51 to 3.78 liters base membrane.)

#### OR

1 quart LD51 to 5 gallons base membrane (0.95 liters LD51 to 18.9 liters base membrane)

The pot life of the resulting thixotropic compound is approximately 1-3 hours at 75°F (24°C) and 50% relative humidity.

#### Limitations:

Not recommended for indoor applications. Should be used in well-ventilated areas due to its strong odor. Containers that have been opened must be used within 1-3 hours. LD51 may react with atmospheric moisture and render it unusable. Do not dilute under any circumstance.

#### Warning:

This product contains Curatives.

This product is considered Dangerous Goods. DOT regulations classify it as: UN 1760, CORROSIVE LIQUID N.O.S., (Contains Amine), Class 8, PG III.

