

# TREMproof® TRA Sheeting

Reinforced Flashing Membrane Embedded in TREMproof 250GC

## **Product Description**

TREMproof® TRA Sheeting is a protective waterproofing course that is compounded from a blend of EPDM and SBR thermostat elastomers. This sheet is reinforced with a high-strength, polyester-woven scrim.

## **Basic Uses**

TREMproof TRA Elastomeric Sheeting is designed to provide a durable, flexible, tear-resistant bridge in areas of high movement where cold and hotapplied membranes are being utilized. TRA Elastomeric Sheeting can also be used as a secondary layer of waterproofing for the TREMproof 250GC Cold-Applied, Heavy-Duty Waterproofing System.

# **Features & Benefits**

- · EPDM/SBR blend provides flexibility for ease of installation
- Woven polyester scrim for added durability and puncture resistance
- TRA Sheeting has the versatility to be utilized in TREMproof® 250GC applications.
- TRA sheeting provides an additional waterproofing layer for ultimate protection
- Superior tensile and tear strength for high stress, heavy-duty applications

## **Availability**

Immediately available from your local Tremco Sales Representative, Tremco Distributor or Tremco Warehouse.

# **Packaging**

12" (305 mm), 18" (457 mm), 24" (610 mm) and 36" (914 mm) x 50' (15.24 m) rolls

60" (1524 mm) x 100' (30.48 m) rolls

#### **Storage**

TREMproof TRA Sheeting should be stored out of direct sunlight. Vertical storage recommended.

#### Limitations

• Not for use beneath sand-set vehicular pavers.

#### **Warranty**

Tremco warrants its Products to be free of defects in materials, but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Tremco makes no other warranty, expressed or implied, including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE, with respect to Tremco Products. Tremco's sole obligation shall be, at its option, to replace or to refund the purchase price of the quantity of Tremco Product proven to be defective, and Tremco shall not be liable for any loss or damage.

Please refer to our website at <a href="www.tremcosealants.com">www.tremcosealants.com</a> for the most up-to-date Product Data Sheets.

NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.

TYPICAL PHYSICAL PROPERTIES		
PROPERTY	TEST METHOD	TYPICAL VALUES
Color		Black
Thickness	ASTM D751-89	0.045" (1.1 mm)
Weight	ASTM D751-89	$41.6 \text{ oz} / \text{yd}^2 (1422 \text{ g} / \text{m}^2)$
Breaking Strength	ASTM D751-89	261 lbf (1446 N) MD 150 lbf (1288 N) XMD)
Tear Strength	ASTM D751-89	94 lbf (313 N) MD 59 lbf (348 N) XMD
Low Temperature Flexibility ( -40 °F)	ASTM D2136- 84	Pass



0817/TRADS-BG

Please refer to our website at www.tremcosealants.com for the most up-to-date application instructions.