

SEALMASTIC™ Emulsion

Dampproofing

DESCRIPTION

SEALMASTIC TYPE I (spray-grade) is an asphalt-based, non-fibred, clay emulsion. Under normal use, it resists flow or sag. Its greater resistance to water is ideal where spray application is desired.

SEALMASTIC TYPE II (brush-on/spray-grade) is an asphalt-based, clay emulsion with fibers specifically formulated to offer a tight film that combines both excellent strength and resistance to water.

SEALMASTIC TYPE III (trowel-on grade) is a trowel-applied mineral colloid, asphalt emulsion, fibrated with selected fibers and produced in an ideal, light trowel application consistency. SEALMASTIC TYPE III offers high weather, water, corrosion, and abrasion resistance. It can be used as an adhesive on foam board installations.

USES

SEALMASTIC emulsion-type dampproofing coatings are ideal for reducing dampness and moisture infiltration through foundation walls, parapets, firewalls, tanks, culverts, cisterns, and bridge abutments. They are also applicable for stone-backing, above-grade cavity wall applications, and below-grade masonry wall dampproofing. The SEALMASTIC product line also helps to minimize internal structural damage from mildew and mold, and is compatible with ICF foam forms.

FEATURES/BENEFITS

- Adheres to damp or “green” surfaces ... no waiting for concrete to thoroughly dry.
- Ready to use ... no heating or thinning required; dries rapidly.
- Fast and economical way to protect concrete and masonry foundation walls from moisture penetration.
- Easy to apply ... available in spray-, brush- or trowel-grades; meets a broad application range.
- Three application grades available for maximum versatility.
- VOC compliant.

PACKAGING

5 Gallon (18.9 Liter) Pails
55 Gallon (208.2 Liter) Drums

COVERAGE

SEALMASTIC TYPE I:

Approximately 70 - 100 ft.²/gal. (1.7 - 2.5 m²/L) per coat.

SEALMASTIC TYPE II/SEALMASTIC TYPE III:
Exterior below-grade dense surfaces, exterior below-grade porous surfaces, exterior above-grade surfaces
Approximately 40 - 50 ft.²/gal. (0.1 - 1.2 m²/L) (30 mils wet).

Coverage may vary due to porosity and condition of concrete.

SHELF LIFE

When stored indoors in original, unopened containers at temperatures between 40° - 90° F, optimum performance and best use is obtained within one year of date of manufacture.

SPECIFICATIONS

TYPE I	ASTM D1187, Type I ASTM D1227, Type III, Class 1
TYPE II	ASTM D1187, Type I ASTM D1227, Type II, Class 1
TYPE III	ASTM D1187, Type I ASTM D1227, Type II, Class 1

All products comply with current federal, state, and local maximum allowable VOC requirements, including U.S. EPA, SCAQMD, and OTC.

TECHNICAL DATA

VOC Content: 0 g/L

APPLICATION

Surface Preparation ... All surfaces to be coated must be thoroughly cleaned of all scale, loose mortar, dust, rust, dirt, oil, grease, and other foreign matter. Use a wire brush, sandblast, or other method in keeping with good construction practices. Before product application, fill voids, cracks, and holes in concrete with cement mortar and allow to dry. If conformance to an ASTM D41 primer is required, use SEALMASTIC SPRAY-MASTIC™ from W. R. MEADOWS. Allow prime-coat to dry tacky to touch prior to application of

CONTINUED ON REVERSE SIDE ...

SEALMASTIC emulsion product. Only apply when temperatures are expected to remain above 50° F (10° C). Do not apply in rain or when rain is threatening for the next 24 hours.

Mixing ... SEALMASTIC TYPE I and SEALMASTIC TYPE II should be thoroughly stirred in their respective containers prior to application. SEALMASTIC TYPE III can be applied directly from the container.

Exterior Below-Grade Dense Surfaces ... Apply SEALMASTIC TYPE II by soft bristle brush or suitable spray equipment or SEALMASTIC TYPE III by trowel. Consult spray equipment manufacturer for instructions.

Product should be applied to properly prepared surfaces in a continuous, unbroken film (free of pinholes), filling and spreading around all joints, slots, and grooves and penetrating into all crevices, chases, reveals, soffits, and corners. Carry coating over the exposed footing's top and outside edge, up to finished grade.

NOTE: Fillers, extenders, and additives in concrete mixes can produce a higher than normal porosity and, as a result, additional coverage coats may be required.

Exterior Below-Grade Porous Surfaces (Three Options):

Membrane System ... For severe conditions or for added protection, apply one coat of SEALMASTIC TYPE II or SEALMASTIC TYPE III. Within four hours, apply REINFORCING FABRIC HCR from W. R. MEADOWS over all coating surfaces. Overlap all edges 3" (76.2 mm) minimum. Press firmly into place without wrinkles. Application of second coat of SEALMASTIC TYPE II or SEALMASTIC TYPE III should be within 24 hours.

Two-Coat System ... If conformance to an ASTM D41 primer is not required, use MEL-PRIME™ W/B from W. R. MEADOWS or a diluted coat of SEALMASTIC emulsion product one to one. Allow prime coat to dry tacky to touch and then apply SEALMASTIC TYPE III in one coat, as described above.

Parge-Coat System ... Before application of SEALMASTIC, a parge-coat of cement mortar should be applied to the block wall. This coat should cover the bottom of the footings to grade level, forming a cove at the junction of the wall and footing. Once the parge-coat cures, apply one trowel-coat of SEALMASTIC TYPE III or two spray- or brush-coats of SEALMASTIC TYPE II as described above.

Backfilling ... Backfilling should be done within 24 - 48 hours after application. No longer than seven days maximum should elapse. Be careful not to damage or rupture the film or displace coating or membranes. To assure maximum protection, PROTECTION COURSE and MEL-DRAIN™ from W. R. MEADOWS should be used. Prolonged exposure to ultraviolet light should be minimized.

Interior Above-Grade Surfaces ...

SEALMASTIC TYPE I, SEALMASTIC TYPE II, and SEALMASTIC TYPE III can be used individually or in combination for dampproofing the exterior face of interior walls in cavity wall construction.

Cleanup ... While still wet, material may be removed with soap and water. Once dried, the material can be removed with kerosene or petroleum naphtha. Solvent manufacturer precautions should be adhered to when using a solvent for cleanup.

PRECAUTIONS

Keep from freezing in the original container. Not intended as a waterproofing membrane. (Refer to MEL-ROL® or MEL-ROL LM from W. R. MEADOWS.) Maximum UV exposure time is 14 days. Maximum in-service temperature is 165° F (74° C). Read and follow application information and precautions. Refer to Safety Data Sheet for complete health and safety information.

LEED INFORMATION

- May help contribute to LEED credits:
- EAp2: Minimum Energy Performance
 - EAc2: Optimize Energy Performance
 - MRc9: Construction and Demolition Waste Management
 - EQc2: Low-Emitting Materials [For Healthcare and Schools (exterior-applied products) ONLY]

For most current data sheet, further LEED information, and SDS, visit www.wrmeadows.com.

LIMITED WARRANTY

W. R. MEADOWS, INC. warrants at the time and place we make shipment, our material will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. Read complete warranty. Copy furnished upon request.

Disclaimer

The information contained herein is included for illustrative purposes only, and to the best of our knowledge, is accurate and reliable. W. R. MEADOWS, INC. cannot however under any circumstances make any guarantee of results or assume any obligation or liability in connection



with the use of this information. As W. R. MEADOWS, INC. has no control over the use to which others may put its product, it is recommended that the products be tested to determine if suitable for specific application and/or our information is valid in a particular circumstance. Responsibility remains with the architect or engineer, contractor and owner for the design, application and proper installation of each product. Specifier and user shall determine the suitability of products for specific application and assume all responsibilities in connection therewith.