

MasterSeal[®] AWB 970 NP

Flashing membrane

PACKAGING

MasterSeal[®] AWB 970 NP 4:
4" x 75' (10.2 cm x 22.9 m) rolls
9 rolls per carton

MasterSeal[®] AWB 970 NP 6:
6" x 75' (15.24 cm x 22.9 m) rolls
6 rolls per carton

MasterSeal[®] AWB 970 NP 9:
9" x 75' (22.9 cm x 22.9 m) rolls
4 rolls per carton

COVERAGE

MasterSeal[®] AWB 970 NP 4:
675 Lin ft (205.7 Lin m) per carton

MasterSeal[®] AWB 970 NP 6:
450 Lin ft (137.2 Lin m) per carton

MasterSeal[®] AWB 970 NP 9:
300 Lin ft (91.4 Lin m) per carton

SHELF LIFE

2 years when stored in original container or
factory sealed packaging as directed

DESCRIPTION

MasterSeal[®] AWB 970 NP is a 20-mil thick, self-adhering, self-sealing, composite membrane of polyester fabric and butyl adhesive. MasterSeal[®] AWB 970 NP is supplied in rolls, on release paper, for easy application.

USES

1. Used as an air barrier accessory to connect different air barrier materials or assemblies together to make the air barrier continuous.
2. Flashing at sills, approved sheathing joints, rough openings, and terminations.
3. As an expansion joint seal.

ADVANTAGES

Primerless application

180-day UV exposure

Remains flexible over time

Meets AAMA 711-13

MasterSeal[®] AWB 970 NP is approved for use on these acceptable substrates and other surfaces:

1. Wood framing (Note: Verify adhesion before applying to wood that has been treated in any way.)
2. ASTM C1177 sheathings, e.g. eXP[™], GlasRoc[®], Securock[™] and DensGlass[™]
3. Water-resistant core gypsum sheathing (ASTM C79/ASTM C1396)
4. Cement-board (ASTM C1325 Type A Exterior)
5. Masonry
6. Exposure 1 or exterior plywood sheathing
7. Exposure 1 OSB
8. Steel framing
9. MasterSeal[®] AWB 970 NP
10. Master Builders Solutions Air / Water-Resistive / Vapor Barriers and Master Builders Solutions Wall System's Air / Water-Resistive / Vapor Barriers and Base Coats.

PROPERTY	ASTM TEST METHOD	RESULTS
Peel Adhesion (Glass Mat Sheathing)	ASTM D3330	83.4 lbs/in
Nail Sealability	ASTM D1970	Passes (no water penetration)
Cold Temperature Pliability	ASTM C765	Passes
Tensile Strength	ASTM D1970	Passes
Accelerated aging	ASTM D3330	4.2 lbf/in
Thermal cycling	ASTM D3330	5.3 lbf/in
Resistance to peel	AAMA 711-13	Pass

PREPARATION

- Acceptable substrate shall be dry, clean, sound and free of releasing agents, paint, contaminants, residue or other coatings. Verify substrate is flat, free of fins or anything that would hinder the adhesion of the membrane.
- Unsatisfactory conditions shall be reported to the general contractor and corrected before application of the Master Builders Solutions Construction System materials.
- A primer such as 3M Super 77 can be applied to enhance adhesion if difficulty is encountered with tape sticking to the substrate.
- Wrap openings in accordance with Master Builders Solutions Air/Water-Resistive/Vapor Barrier application guidelines and technical bulletin.
- If blisters occur, they can be slit with a utility knife and the MasterSeal® AWB 970 NP pressed flat with a roller. Ensure no voids or holes are present. Repair as necessary.
- Installed materials should be checked for delamination of edges before final system application. Repair as necessary.
- Overlap MasterSeal® AWB 970 NP a minimum of 2" (50 mm) horizontally and 6" (150 mm) vertically.
- Ensure MasterSeal AWB 970 NP is coated with Master Builders Solutions Air/Water-resistive/Vapor Barrier after application
- Install exterior cladding system in accordance with manufacturer's current specifications and details.
NOTE: Provide sufficient slack at expansion joints to allow for movement.
- Do not store rolls on end.
- Protect from rain and physical damage until installation of exterior cladding system.
- Do not apply the material to any surfaces not listed as an acceptable substrate/ surface, including silicone caulk or other solvent based products.
- Do not expose material to sunlight for over 180 days.
- Apply MasterSeal® AWB 970 NP only to dry surfaces. Allow surfaces to dry a minimum of 24 hours after precipitation.

SHIPPING AND STORAGE

Protect Master Builders Solutions materials during transportation and installation to avoid physical damage. Store Master Builders Solutions materials in a cool, dry place protected from freezing. Protect from extreme heat, over 90°F (32°C), and direct sunlight.

APPLICATION

- Cut MasterSeal® AWB 970 NP roll to desired length with a utility knife or scissors.
- Peel back sufficient length of release paper immediately before application and center the MasterSeal® AWB 970 NP over the area to be sealed.
- Using a wallpaper roller, extension-handled countertop roller or weighted hand roller, firmly roll the MasterSeal® AWB 970 NP to the area being sealed. As the MasterSeal® AWB 970 NP is applied, pull more of the release film, exposing the adhesive surface, pressing down with a roller and keeping the MasterSeal® AWB 970 NP smooth.

FOR BEST PERFORMANCE

- Do not apply Master Builders Solutions construction systems materials in ambient temperatures below 4°C (40°F). Provide supplementary heat during installation and drying period (at least 24 hours after installation and until dry) when temperatures less than 4°C (40°F) are anticipated).
- When applying the membrane in cooler temperatures, store material for 24 hours inside at room temperature for better adhesion. Adhesion properties of MasterSeal® AWB 970 NP during application in cooler temperatures may also be improved by the use of a heat gun

TECHNICAL SUPPORT

Consult the Master Builders Solutions Construction Systems Technical Services Department for specific recommendations concerning all other applications. Consult the Master Builders website, www.master-builders-solutions.com, for additional information about products and systems and for updated literature.

LIMITED WARRANTY NOTICE

Master Builders Solutions Construction Systems US, LLC ("Master Builders") warrants this product to be free from manufacturing defects and to meet the technical properties on the current Technical Data Guide, if used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control. Master Builders MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS. The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is shipment to purchaser of product equal to the amount of product that fails to meet this warranty or refund of the original purchase price of product that fails to meet this warranty, at the sole option of Master Builders. Any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. Master Builders WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on Master Builders' present knowledge and experience. However, Master Builders assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. Master Builders reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.

FOR PROFESSIONAL USE ONLY. NOT FOR SALE TO OR USE BY THE GENERAL PUBLIC

