

Sikaflex® Sealant/Adhesive Primers

Sikaflex Primers 260, 429, and 449

Description	Sikaflex primers are special materials formulated to improve the bond of Sikaflex urethane sealants when applied to specific substrates.						
Sikaflex Primer 260	Sikaflex Primer 260 promotes adhesion of urethane sealants to various metallic, non-metallic, and plastic substrates.						
Sikaflex Primer 429	Sikaflex Primer 429 promotes adhesion to clean, sound, and dry concrete, masonry, Exterior Insulation Finish Systems (EIFS), and wood — including teak and mahogany.						
Sikaflex Primer 449	Sikaflex Primer 449 is used to promote adhesion to pvc, solvent-based enamel, PPG's fluorocarbon Duranar-finish, and certain plastics such as ABS and Plexiglass.						
Where to Use	Most substrates require a primer only if testing shows need for it or where the sealant will be underwater after cure. Certain substrates do require a primer under all conditions.						
Advantages	<ul style="list-style-type: none"> ■ Single-component, ready to use. ■ Easily applied by brush, dauber, or spray. 						
Coverage	<p>Following are average coverages, depending on porosity of substrate:</p> <p>Sikaflex Primer Coverage per pint (Liner ft. 1/2" x 1/2" joint)</p> <table border="1"> <tr> <td>260</td> <td>300-500</td> </tr> <tr> <td>429</td> <td>300</td> </tr> <tr> <td>449</td> <td>300-500</td> </tr> </table>	260	300-500	429	300	449	300-500
260	300-500						
429	300						
449	300-500						
Packaging	<p>Sikaflex 260 and 449 primers are available in pints, 6/carton.</p> <p>Sikaflex 429 primer is available in pints, 6/carton; and gallons, 2/carton.</p>						

Construction

Substrate	Primer Required	Recommended primer if necessary
Concrete and Masonry		
Concrete Block	No	Sikaflex 429 primer
Placed Concrete	No	Sikaflex 429 primer
Precast Concrete	No	Sikaflex 429 primer
Mortar	No	Sikaflex 429 primer
Grout	No	Sikaflex 429 primer
Brick	No	Sikaflex 429 primer
SikaTops	No	Sikaflex 429 primer
Stone		
Granite	No	Sikaflex 429 primer
Marble	No	Sikaflex 260 primer
Paints		
Acrylic Latex	No Bond Achieved	
Emercoat 33	No Bond Achieved	
DeSoto Fluoropon	No Bond Achieved	
PPG Duracon S600	No Bond Achieved	
Solvent-based Enamel	Yes	Sikaflex 449 primer
PPG Fluorocarbon	Yes	Sikaflex 449 primer
Duranar	Yes	Sikaflex 449 primer
PPG Polycron	Yes	Sikaflex 449 primer
Kynar	Yes	Sikaflex 449 primer
Siliconized Polyester	Yes	Sikaflex 260 primer
Alucobond	Yes	Sikaflex 260 primer
Plastics		
PVC	Yes	Sikaflex 449 primer
ABS	Yes	Sikaflex 449 primer
Plexiglass	Yes	Sikaflex 449 primer
Plexiglass DR	Yes	Sikaflex 449 primer
Lucite	Yes	Sikaflex 449 primer
Rovel Plastic	Yes	Sikaflex 449 primer

Substrate	Primer Required	Recommended primer if necessary
Plastics cont'd		
Lexan	Yes	Sikaflex 260 primer
Teflon	No Bond Achieved	
Polyethylene	No Bond Achieved	
Polypropylene	No Bond Achieved	
Tuffak	Yes	Sikaflex 449 primer
Polyester/Fiberglass	No	Sikaflex 449 primer
Glass		
Glass - Sheet, float or plate	No	Sikaflex 260 primer
Porcelain	No	Sikaflex 260 primer
Ceramic tile	No	Sikaflex 260 primer
Metals		
Aluminum - Anodized	No	Sikaflex 260 primer
Aluminum - Mill Finish	Yes	Sikaflex 260 primer
Lead	No	Sikaflex 260 primer
Copper (bright/clean)	No	Sikaflex 260 primer
Brass	No	Sikaflex 260 primer
Zinc	No	Sikaflex 260 primer
Tinplate	No	Sikaflex 260 primer
Steel (Bright/Clean)	No	Sikaflex 260 primer
Steel - Stainless	Yes	Sikaflex 260 primer
Steel - Galvanized	Yes	Sikaflex 260 primer
Rubber		
Urethane	No	Sikaflex 449 primer
Woods		
Unfinished Woods	No	Sikaflex 429 primer
EIFS**		
Dryvit	Yes	Sikaflex 429 primer
Sto	Yes	Sikaflex 429 primer
Synergy	Yes	Sikaflex 429 primer

** Product will bond without primer however primer is recommended by EIFS manufacturers to properly seal substrate. Follow EIFS manufacturer's primer recommendations.

Typical Data (Material and curing conditions 73°F and 50% R.H.)

RESULTS MAY DIFFER BASED UPON STATISTICAL VARIATIONS DEPENDING UPON MIXING METHODS AND EQUIPMENT, TEMPERATURE, APPLICATION METHODS, TEST METHODS, ACTUAL SITE CONDITIONS AND CURING CONDITIONS.

Color Clear
Shelf life 6 months in original, unopened containers.



How to Use Surface Preparation

The key to good bonding with Sikaflex sealants/primers is surface preparation. Specifically, all surfaces must be dry and free of dirt, grease, mold release agents, loose mortar, laitance, and any foreign matter. If the joint contains old sealant, it and all extraneous material must be removed and the substrate cleaned by mechanical means. Apply primers at substrate temperatures of 40°F and rising. Surface must be frost free.

Application

Shake or stir primer well before using. Apply to dry, clean, oil free surface with a brush, dauber or spray.

Sikaflex Primer	Dry time before installing sealant	
260	>1 hr.	<8 hrs.*
429	>1 hr.	<8 hrs.*
449	>30 min.	<8 hrs.*

* If sealant cannot be installed within 8 hours of priming, reprime.

Limitations

- Primer should not be used if it starts to gel in container.
- Protect Sikaflex primers from moisture. Once container has been opened, use contents immediately.
- Do not attempt to use partial containers.
- Do not reseal or reuse. Resealing may cause moisture contamination and gelling.

Caution

Sikaflex Primer 260

Flammable; Irritant; Poison - Contains methanol. May cause skin/eye/respiratory irritation. Avoid contact. Methanol is a poison and may cause blindness if ingested. Use only with adequate ventilation. Use of safety goggles and chemical resistant gloves is recommended. In case of exceedance of PELs, use an appropriate, properly fitted NIOSH approved respirator. Remove contaminated clothing. Keep away from heat, sparks, and open flames.

Sikaflex Primer 429

Flammable; Irritant; Sensitizer - Contains aromatic polyisocyanate, xylene, PGMEA, TDI. May cause skin/eye/respiratory irritation. May cause skin and/or respiratory sensitization after prolonged or repeated contact. Avoid contact. May cause headaches, dizziness or other CNS effects. TDI is a suspect carcinogen (IARC, NTP). Use only with adequate ventilation. Use of safety goggles and chemical resistant gloves is recommended. In case of exceedance of PELs, use an appropriate, properly fitted NIOSH approved respirator. Remove contaminated clothing. Keep away from heat, sparks, and open flames.

Sikaflex Primer 449

Flammable; Irritant; Sensitizer - Contains xylene, butyl acetate, methylethyl ketone, toluene. May cause skin/eye/respiratory irritation. May cause skin and/or respiratory sensitization after prolonged or repeated contact. Avoid contact. May cause headaches, dizziness or other CNS effects. Use only with adequate ventilation. Use of safety goggles and chemical resistant gloves is recommended. In case of exceedance of PELs, use an appropriate, properly fitted NIOSH approved respirator. Remove contaminated clothing. Keep away from heat, sparks, and open flames.

First Aid

In case of skin contact, wash immediately and thoroughly with soap and water. If symptoms persist, consult physician. For eye contact, flush immediately with plenty of water for at least 15 minutes; contact a physician. For respiratory problems, remove person to fresh air; if symptoms persist, consult physician. In case of ingestion, consult a physician immediately - methanol is a poison. Remove contaminated clothing.

Clean Up

In case of spill or leaks, wear suitable protective equipment, contain spill, collect with absorbent material, and transfer to suitable container. Ventilate area. Avoid contact. Dispose of in accordance with current, applicable, local, state and federal regulations.

KEEP CONTAINER TIGHTLY CLOSED • KEEP OUT OF REACH OF CHILDREN • NOT FOR INTERNAL CONSUMPTION • FOR INDUSTRIAL USE ONLY
All information provided by Sika Corporation ("Sika") concerning Sika products, including but not limited to, any recommendations and advice relating to the application and use of Sika products, is given in good faith based on Sika's current experience and knowledge of its products when properly stored, handled and applied under normal conditions in accordance with Sika's instructions. In practice, the differences in materials, substrates, storage and handling conditions, actual site conditions and other factors outside of Sika's control are such that Sika assumes no liability for the provision of such information, advice, recommendations or instructions related to its products, nor shall any legal relationship be created by or arise from the provision of such information, advice, recommendations or instructions related to its products. The user of the Sika product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with the full application of the product(s). Sika reserves the right to change the properties of its products without notice. All sales of Sika product(s) are subject to its current terms and conditions of sale which are available at www.sikausa.com or by calling 800-933-7452.

Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Technical Data Sheet, product label and Material Safety Data Sheet which are available online at www.sikausa.com or by calling Sika's Technical Service Department at 800-933-7452. Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instruction for each Sika product as set forth in the current Technical Data Sheet, product label and Material Safety Data Sheet prior to product use.

LIMITED WARRANTY: Sika warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Technical Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKASHALL NOT BELIEVABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKASHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Visit our website at www.sikausa.com

1-800-933-SIKA NATIONWIDE

Regional Information and Sales Centers. For the location of your nearest Sika sales office, contact your regional center.

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: 800-933-7452
Fax: 201-933-6225

Sika Canada Inc.
601 Delmar Avenue
Pointe Claire
Quebec H9R 4A9
Phone: 514-697-2610
Fax: 514-694-2792

Sika Mexicana S.A. de C.V.
Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



Sika and Sikaflex are registered trademarks.
Printed in Canada.

