

Application Procedure: MasterSeal[®] NP 2™

This procedure covers the preparation and application of **MasterSeal[®] NP 2™**, a three-component, highly flexible, non-priming, high-performance polyurethane sealant.

1. Joint Preparation:

- 1.1. The number of joints and the joint width should be designed for a maximum of ±25% movement.
- 1.2. The depth of the sealant should be one-half the width of the joint. The maximum depth is 13 mm (1/2") and the minimum is 6 mm (1/4") Maximum recommended joint width is 50mm (2"). Refer to Table 1.

Table 1:

Joint Width and Sealant Depth

JOINT WIDTH, IN (MM)	SEALANT DEPTH AT MIDPOINT, IN (MM)
1/4 - 1/2 (6 – 13)	1/4 (6)
1/2 - 3/4 (13 – 19)	1/4 - 3/8 (6 – 10)
3/4 - 1 (19 – 25)	3/8 – 1/2 (10 – 13)
1 – 1-1/2 (25 – 38)	1/2 (13)

- 1.3. In deep joints, the sealant depth must be controlled by Closed-Cell Backer-Rod or Soft Backer- Rod. Where the joint depth does not permit the use of backer-rod, a bondbreaker (polyethylene strip) must be used to prevent three-sided adhesion. For horizontal joints, use Closed Cell Backer Rod.
- 1.4. To maintain the recommended sealant depth, install backer-rod by compressing and rolling it into the joint channel without stretching it lengthwise. Closed-Cell Backer-Rod should be about 3 mm (1/8") larger in diameter than the width of the joint to allow for compression. Soft Backer-Rod should be approximately 25% larger in diameter than the joint width. The sealant does not adhere to it, and no separate bondbreaker is required.
- 1.5. Do not use multiple twisted backer rod.
- 1.6. Do not prime or puncture the backer-rod.

2. Surface Preparation:

- 2.1. CONCRETE, STONE, AND OTHER MASONRY - Clean by grinding, sandblasting, or wire brushing to expose a sound surface free of contamination and laitance.

- 2.2. WOOD - New and weathered wood must be clean and sound. Scrape away loose paint to bare wood. Any coating that cannot be removed must be tested to verify adhesion of sealant or determine an appropriate primer.
- 2.3. METAL - Remove scale, rust, and coatings from metal to expose a bright white surface. Remove protective coatings as well as any chemical residue or film. Aluminium window frames are frequently coated with a clear lacquer that must be removed before the application of **MasterSeal® NP 2™**.

Any coating that cannot be removed must be tested to verify adhesion of sealant or determine an appropriate primer. Remove any other protective coatings or finishes that could interfere with adhesion.

3. Priming:

- 3.1. **MasterSeal® NP 2™** is generally considered a non-priming sealant, but special circumstances or substrates may require a primer. It is the user's responsibility to check the adhesion of the cured sealant on typical test joints at the project site before and during application. Refer to product data sheet on **MasterSeal P 101** and consult Technical Service for additional information.
- 3.2. For immersion applications, **MasterSeal P 101** must be used.
- 3.3. Apply primer full strength with a brush or clean cloth. A light, uniform coating is sufficient for most surfaces. Porous surfaces require more primer; however, do not over apply.
- 3.4. Allow primer to dry before applying **MasterSeal® NP 2™**. Depending on temperature and humidity, primer will be tack free in 15 – 120 minutes. Priming and sealing must be done on the same work day.

4. Mixing

- 4.1 **MasterSeal® NP 2™** is a three-component system and must be thoroughly mixed before use. The oversize PTA container allows for the addition and mixing of PTB and Sonolastic® color pigment into PTA. 5.67 L unit: Transfer entire contents of PTB to PTA container using a spatula or a margin trowel.
- 4.2. It is imperative that PTB be mixed thoroughly with PTA. Before adding Sonolastic® pigment, scrape sides of container to ensure complete mixing of PTA and PTB.
- 4.3. With a slow-speed drill and a sealant mixing paddle, mix 4 – 6 minutes. The paddle blade must be kept below the surface of the sealant to avoid whipping air into the sealant.
- 4.4. Transfer the entire contents of the Sonolastic® pigment can into the mixed PTA and PTB. Use a spatula or knife to remove all the pigment from the container.
- 4.5. Continue mixing with a slow-speed (500 – 600 rpm) drill and slotted paddle until color is uniform.
- 4.6. The pot life of mixed **MasterSeal® NP 2™** is influenced by temperature.

5. Application

- 5.1. Except when unusual job conditions dictate the use of knife or spatula, apply **MasterSeal® NP 2™** by professional bulk gun loaded at the jobsite. Fill joints from the bottom up to the exterior face by holding a properly sized nozzle against the joint bottom.
- 5.2. Proper tooling ensures the correct bead configuration and a neat joint. Equally important, it ensures maximum adhesion to the sides of the joint. For best results,
- 5.3. Best practices dictate that all caulking and sealing be done when temperatures are above 40° F (4°C) to avoid application to moisture-laden surfaces.
- 5.4. Moisture on substrates will adversely affect adhesion.
- 5.5. Application may proceed as low as 20°F (-6°C) if there is certainty that substrates are completely dry, free of moisture, and clean as described under Surface Preparation.

6. Clean Up:

- 6.1. Immediately after use and before sealant has cured, clean equipment with a suitable thinner (Xylene / MEK / Acetone).
- 6.2. Cured sealant may be removed by cutting with a sharp-edged tool; thin films by abrading.

7. Curing:

- 7.1. **MasterSeal® NP 2™** cures by a chemically controlled reaction. Initial cure is within 24 hours, and complete cure takes approximately 7 days. Allow 14 days cure at 70°F (23°C) prior to water immersion.
- 7.2. Cure rates are dependent on temperature and humidity.
- 7.3. **MasterSeal® NP 2™** cures by a chemically controlled reaction. Initial cure is within 24 hours, and complete cure takes approximately 7 days. Allow 14 days cure at 70° F (23°C) prior to water immersion.
- 7.4. Cure rates are dependent on temperature and humidity.

8. For Best Performance:

- 8.1. Pursuant to accepted industry standards and practices, using rigid paints and/or coatings over flexible sealants can result in a loss of adhesion of the applied paint and/or coating, due to the potential movement of the sealant. However, should painting and/or coating be desired it is required that the applicator of the paint and/or coating conduct on-site testing to determine compatibility and adhesion.

- 8.2. Do not allow uncured **MasterSeal® NP 2™** to come into contact with alcohol-based materials or solvents.
- 8.3. Do not apply polyurethane sealants in the vicinity of uncured silicone sealants or uncured **Sonolastic 150** with VLM Technology or 150 Tint Base.
- 8.4. **MasterSeal® NP 2™** should not come in contact with oil-based caulking, silicone sealants, polysulfides or fillers impregnated with oil, asphalt, or tar.
- 8.5. Do not apply epoxy-based coatings in the vicinity of uncured **MasterSeal® NP 2™**.
- 8.6. Do not apply to freshly treated wood; treated wood must have weathered for at least 6 months.
- 8.7. Do not open containers until ready for use.
- 8.8. Units are premeasured; do not use partial units.
- 8.9. **MasterSeal® NP 2™** may yellow in the presence of unvented artificial heat; this is a surface phenomenon that does not affect sealant performance.
- 8.10. When **MasterSeal® NP 2™** is to be used in areas subject to continuous water immersion, cure for 14 days at 70°F (23°C). Allow longer cure times at lower temperatures. Always use **MasterSeal P 101**.
- 8.11. Do not use in swimming pools, or on other submerged conditions where the sealant will be exposed to strong oxidizers. Avoid submerged conditions where water temperatures will exceed 120°F (50°C).
- 8.12. Horizontal joints subject to traffic or intermittent ponding of water require the use of primer. Call Technical Service for details.
- 8.13. Substrates such as copper, stainless, and galvanized typically require the use of a primer; An adhesion test is recommended for any other questionable substrate.
- 8.14. Do not use as a cap, heel or toe bead for exterior glazing.
- 8.15. Use only color packs designed for use with **MasterSeal® NP 2™**.
- 8.16. Make certain the most current versions of product data sheet and MSDS are being used; call Customer Service to verify the most current version.
- 8.17. Proper application is the responsibility of the user. Field visits by Master Builder Solutions personnel are for the purpose of making technical recommendations only and not for supervising or providing quality control on the jobsite.

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by Master Builders Solutions either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Master Builders Solutions, are responsible for carrying out procedures appropriate to a specific application.
