

# Reinforcing Mesh

Balanced, open-weave glass fiber reinforcing mesh

## COLOR

Senergy meshes are white, except 4" and 9" Sheathing Fabric which are gray.

## DESCRIPTION

Balanced, open-weave glass fiber reinforcing mesh, twisted multi-end strands treated for compatibility with Senergy Base Coats. A variety of Reinforcing Mesh types are available to meet the different requirements of impact resistance at specific wall locations. Senergy Self-Adhering Mesh tape, in addition to having the same properties as described above, is coated with a pressure sensitive adhesive.

## USES

1. For use with all Senerflex Wall Systems and Senturion Wall Systems, Senergy Surfacing Systems and Senergy Cement-Board Stucco Systems and for EPS shapes on Senergy Stucco Wall System that use either EPS or polyisocyanurate insulation boards and for use over EPS shapes on all Senergy Wall Systems.
2. For above ground use with all Senergy Surfacing Systems.
3. Senergy Self-Adhering Mesh tape only: reinforces Senershield over acceptable sheathing joints and reinforces Senershield over rough openings and at terminations.
4. Fiberlath Mesh only: reinforces and provides a keying device for base coat on Senerthik Class PM EIFS.
5. 4", 9" sheathing Fabric only: reinforces Senershield-R or Senershield-VB over acceptable sheathing joints and reinforces Senershield-R or Senershield-VB over rough openings and terminations.

## APPLICATION

### CORNER MESH:

Install Corner Mesh at exterior corners. Apply mixed Base Coat to insulation board at outside corners. Immediately embed the Corner Mesh into the Base Coat by troweling from the corner; butt edges and avoid wrinkles. After Base Coat is dry and hard, apply a layer of Flexguard 4, Intermediate 6 or 12 Reinforcing Mesh over the entire surface of the Corner Mesh.

### FLEXGUARD 4, INTERMEDIATE 6 AND 12 REINFORCING MESHES:

Fully embed clean mesh into wet base coat and smooth with a trowel so as to achieve mesh embedment with no mesh color visible. Double layers of Flexguard 4 and Intermediate 6 mesh must be applied at all inside and outside corners. Window corners also require secondary reinforcement as per details. Lap Reinforcing Mesh 64 mm (2 1/2") minimum at edges.

## ADVANTAGES

Alkali resistance, compatibility with all Senergy Base Coats; maintains tensile strength and flexibility for long-term durability; all glass fiber reinforcing mesh complies with ASTM E2098

Senergy Self-Adhering Mesh TAPE; simplifies and speeds application of Senershield Water-Resistive Barrier

**STRONG 15 AND HI-IMPACT 20 REINFORCING MESHES:**

Embed Strong 15 or Hi-Impact 20 Reinforcing Mesh in wet base coat by troweling from the center to the edges. Butt strong 15 or Hi-Impact 20 Reinforcing Mesh at all adjoining edges, do not use to backwrap or bend around corners. Butt strong 15 or Hi-Impact 20 Reinforcing Mesh at adjoining edges of Corner Mesh. Ensure Reinforcing Mesh is free of wrinkles and embedded in Base Coat so that no Reinforcing Mesh color is visible. After Base Coat with embedded Reinforcing Mesh is dry and hard (normally 8 to 10 hours), apply a layer of Flexguard 4 or Intermediate 6 Reinforcing Mesh over the entire surface to achieve total nominal Base Coat/Reinforcing Mesh thickness of 2.4 mm (3/32").

**SELF-ADHERING MESH TAPE:**

Substrate shall be acceptable to Master Builders Solutions Wall Systems. Substrate shall be dry, clean, sound and free of release agents, paint or other contaminants. Verify that the substrate is flat, free of fins or anything that would hinder adhesion of the mesh. Unsatisfactory conditions shall be reported to the general contractor and corrected before application of the Senergy Wall System. Senergy Self-Adhering Mesh tape may be applied direct from the roll. Center the mesh over the area to be reinforced. Firmly press the mesh onto the surface while unrolling. Avoid creating wrinkles and fish-mouths. If they occur cut out the area with a utility knife and re-apply. Overlap ends of Senergy Self-Adhering Mesh tape a minimum of 63.5 mm (2 1/2"). Cover Self-Adhering Mesh tape with a layer of Senershield.

**4", 9" SHEATHING FABRIC:**

Apply mixed Senershield-R at all sheathing, joints, terminations, inside and outside corners and rough openings. Immediately place and center 4" or 9" Sheathing Fabric over wet Senershield-R or Senershield-VB at outside corners and rough openings. Ensure fabric extends evenly on both sides of the sheathing joint. Lap mesh 63.5 mm (2 1/2") minimum at intersections. Allow to dry to the touch, before applying Senershield-R or Senershield-VB to entire wall surface.

**LIMITATIONS**

1. Protect Senergy Reinforcing Mesh during transportation and installation to avoid physical damage.
2. Store Senergy Reinforcing Mesh in a cool, dry place protected from exposure to moisture.
3. See Senergy Specifications and Details for complete information on installation of Senergy Wall Systems.
4. Apply in temperatures of 4 °C (40 °F) and higher.

**TECHNICAL DATA**

**ASTM E 695 IMPACT RESISTANCE:**

No cracks in the exterior insulation and finish system from a drop height of 1.83 m (6'). Maximum indentation did not exceed 8.5 mm (0.33").

**EIMA IMPACT STANDARD 101.86:**

Flexguard 4/Standard Base Coat	Standard Impact Resistance	[2.8–5.6 J (25–49 inch-lbs)]
Intermediate 6/Standard Base Coat	Standard Impact Resistance	[2.8–5.6 J (25–49 inch-lbs)]
Intermediate 12/Standard Base Coat	Medium Impact Resistance	[5.7–10.1 J (50–89 inch-lbs)]
Intermediate 12 & Flexguard 4/Standard Base Coat	High Impact Resistance	[10.2–17.0 J (90–150 inch-lbs)]
Strong 15 & Flexguard 4/Standard Base Coat	Ultra High Impact Resistance	[over 17.0 J (150 inch-lbs)]
Hi-Impact 20 & Flexguard 4/Standard Base Coat	Ultra High Impact Resistance	[over 17.0 J (150 inch-lbs)]

**DADE COUNTY PROTOCOL 201 IMPACT TESTS (LARGE AND SMALL MISSILE):**

Passed with various wall assemblies. See technical bulletin, *EIFS and Coatings Tests Results*, for details.

**FLEXGUARD 4 REINFORCING MESH:**

A single-layer application of Flexguard 4 provides reinforcement for wall system areas not expected to receive abnormal abuse or traffic.

Weave:	Leno
Weight:	142 g/m <sup>2</sup> (4.2 oz/yd <sup>2</sup> ) +/- 5%
Fabric Count:	6 x 5
Packaging:	96.5 cm x 45.7 m (38" x 150') roll: 475 sf - 44.1 m <sup>2</sup> 9" Starter rolls: 24.1 cm x 45.7 m (9" x 150'): 112.5 sf - 11.0 m <sup>2</sup> 122 cm (48" width): 600 sf - 55.8 m <sup>2</sup> 183 cm (72" width): 900 sf - 83.6 m <sup>2</sup> 244 cm (96" width): 1200 sf - 111.51m <sup>2</sup>

**INTERMEDIATE 6 REINFORCING MESH:**

A single-layer application of Intermediate 6 provides reinforcement for wall system areas not expected to receive abnormal abuse or traffic.

Weave:	Leno
Weight:	190 g/m <sup>2</sup> (5.6 oz/yd <sup>2</sup> ) +/- 5%
Fabric Count:	6 x 5
Packaging:	96.5 cm x 45.7 m (38" x 150') roll: 475 sf - 44.1 m <sup>2</sup>

#### INTERMEDIATE 12 REINFORCING MESH:

A versatile, intermediate weight mesh. While capable of being used for a complete single-layer application, Intermediate 12 is often used in conjunction with Flexguard 4 or Intermediate 6 to offer added impact resistance at specific areas (i.e. around doors or walkways).

Weave: Leno  
Weight: 373 g/m<sup>2</sup> (11 oz/yd<sup>2</sup>) +/- 5%  
Fabric Count: 16 x 12  
Packaging: 96.5 cm x 22.8 m (38" x 75') roll: 237.5 sf - 22.1 m<sup>2</sup>

#### STRONG 15 REINFORCING MESH:

A medium/heavy-weight mesh intended for areas expected to receive traffic and abuse. strong 15 has special installation procedures including:

1. Edges are butted (not overlapped).
2. strong 15 cannot be used for backwrapping and will not bend around corners.
3. An application of strong 15 requires a continuous and lapped Flexguard 4 or Intermediate 6 application as an overlay.

Weave: Hurl Leno  
Weight: 508 g/m<sup>2</sup> (15 oz/yd<sup>2</sup>) + 5%  
Fabric Count: 4 x 4  
Packaging: 96.5 cm x 22.8 m (38" x 75') roll: 237.5 sf - 22.1 m<sup>2</sup>

#### HI-IMPACT 20 REINFORCING MESH:

A heavy-weight mesh intended for areas expected to receive a high degree of traffic and abuse. Hi-Impact 20 has special installation procedures including:

1. Edges are butted (not overlapped).
2. Hi-Impact 20 cannot be used for backwrapping and will not bend around corners.
3. An application of Hi-Impact 20 requires a continuous and lapped Flexguard 4 or Intermediate 6 application as an overlay.

Weave: Hurl Leno  
Weight: 675 g/m<sup>2</sup> (20.0 oz/yd<sup>2</sup>) +/- 5%  
Fabric Count: 4 x 3  
Packaging: 99.0 cm x 22.8 m (39" x 75') roll: 243.75 sf - 22.6 m<sup>2</sup>

#### CORNER MESH:

An intermediate-weight mesh for use at exterior corners when added impact resistance or clean, crisp corners are desired. Corner Mesh is pre-marked for easy bending. An overlay of Flexguard 4, Intermediate 6 or 12 is required when Corner Mesh is used.

Weave: Plain or Hurl  
Weight: 304 g/m<sup>2</sup> (9.0 oz/yd<sup>2</sup>) +/- 5%  
Fabric Count: 12 x 4  
Packaging: 22.9 cm x 45.7 m (9" x 150') roll: 112.5 sf - 10.47 m<sup>2</sup>

#### SELF-ADHERING REINFORCING MESH TAPE:

A standard weight mesh coated with a pressure sensitive adhesive and used with Senersshield water-resistive barrier as reinforcement over acceptable sheathing joints, rough openings and at terminations.

Weave: Leno  
Weight: 169 g/m<sup>2</sup> (5 oz/yd<sup>2</sup>) +/- 10%  
Packaging: 4" Rolls: 10.2 cm x 45.7 m (4" x 150'): 50 sf - 4.66 m<sup>2</sup>  
9" Rolls: 22.9 cm x 45.7 m (9" x 150'): 112.5 sf - 10.47 m<sup>2</sup>

#### 4", 9" SHEATHING FABRIC:

4", 9" sheathing fabric is used with Senersshield-R or Senersshield-VB air/water-resistive barrier as reinforcement over acceptable sheathing joints, rough openings and at terminations.

Packaging: 4" Sheathing Fabric: 10.2 cm x 54.8 m (4" x 180 ft) roll: 60 sf - 5.59 m<sup>2</sup>  
9" Sheathing Fabric: 22.9 cm x 54.8 m (9" x 180 ft) roll: 135 sf - 12.55 m<sup>2</sup>

---

#### HEALTH, SAFETY AND ENVIRONMENTAL

Read, understand and follow all Safety Data Sheets and product label information for this product prior to use. The SDS can be obtained by visiting [senergy.master-builders-solutions.com/en](http://senergy.master-builders-solutions.com/en), e-mailing your request to [mbsbscst@mbcc-group.com](mailto:mbsbscst@mbcc-group.com) or calling +1 (800) 433-9517. Use only as directed.

**IN CASE OF EMERGENCY: Call CHEMTEL +1 (800) 255-3924 or if outside the US or Canada, +1 (813) 248-0585.**

---

#### TECHNICAL SUPPORT

Consult Master Builders Solutions Technical Services Department at +1 (800) 589-1336 for specific recommendations concerning all other applications. Consult the Wall Systems website at [senergy.master-builders-solutions.com/en](http://senergy.master-builders-solutions.com/en), for additional information about products and systems and for updated literature.

---

#### LIMITED WARRANTY NOTICE

Master Builders Solutions Construction Systems US, LLC ("Master Builders") warrants this product to be free from manufacturing defects and to meet the technical properties on the current Technical Data Guide, if used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control. MASTER BUILDERS MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS. The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is shipment to purchaser of product equal to the amount of product that fails to meet this warranty or refund of the original purchase price of product that fails to meet this warranty, at the sole option of Master Builders. Any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. MASTER BUILDERS WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on Master Builders' present knowledge and experience. However, Master Builders assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. Master Builders reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.

**FOR PROFESSIONAL USE ONLY. NOT FOR SALE TO OR USE BY THE GENERAL PUBLIC.**

For the most current version of this literature, please visit our website at [senergy.master-builders-solutions.com/en](http://senergy.master-builders-solutions.com/en).