



# INCRETE HIGH PERFORMANCE EPOXY

## 2-PART EPOXY COATING FOR CONCRETE

### PACKAGING

1 gal (3.8 L) and 3 gal (11.4 L) kits

### YIELD

Coverage/U.S.Gallon (3.78 L)

10 mils 160 ft<sup>2</sup> ( 250 μm 5.0 m<sup>2</sup>)

20 mils 80 ft<sup>2</sup> ( 400 μm 7.5 m<sup>2</sup>)

40 mils 40 ft<sup>2</sup> (1000 μm 3.7 m<sup>2</sup>)

### APPEARANCE

Clear and 35 standard colors

### CLEAN UP

Clean tools and application equipment with INCRETE SOLV-KLEEN, methyl ethyl ketone or acetone immediately after use. Clean spills or drips with solvent while still wet. Dried INCRETE HIGH PERFORMANCE EPOXY will require mechanical abrasion for removal.

### SHELF LIFE

2 years in original, unopened containers

### BRIEF OVERVIEW

INCRETE HIGH PERFORMANCE EPOXY is a 2-component, 100% solids, high-performance coating that provides a high gloss, high-build protection for concrete, rigid surfaces and masonry. Available in clear and in 35 standard colors, this coating offers excellent chemical resistance and superior results against abrasion. Meets federal guidelines for food processing areas.

### PRODUCT CHARACTERISTICS

#### ADVANTAGES

- Versatile: coatings, broadcast floors, chips, INCRETE METAL FX
- High film build and gloss
- Highly chemical resistant
- Stain and scratch resistant
- Low odor

#### COMMON USES

- Warehouse and garage floors
- Food processing, kitchens, food storage areas
- Pharmaceutical plants
- Manufacturing plants/workshops
- Education facilities and hospitals
- Light commercial and industrial facilities
- Counter tops
- Mechanic and body shops
- 50 °F (10 °C) to 90 °F (32 °C)

#### COMMON METHODS

- Trowel
- Roller
- Squeegee
- Brush

### TECHNICAL INFORMATION

\* The following results were developed under laboratory conditions @ 75 °F (24 °C)

<b>Mix Ratio</b> (by Volume) .....	2:1
<b>Gel Time</b> , 200 g, minutes.....	35 to 45
<b>Pot Life</b> , 3 gal (11.4 L), minutes .....	15 to 25
<b>Compressive Strength</b> , ASTM D 695 @ 7 days psi (MPa).....	6,700 (46.2)
<b>Hardness, Shore D</b> , ASTM D 2240 .....	85 to 90
<b>Bond Strength</b> , ASTM D 4541 .....	Greater than concrete
<b>Water Absorption</b> , ASTM D 570 @ 24 hours.....	<0.5%
<b>Monolithic Surfacing</b> , ASTM C 722 .....	Passes
<b>VOC Content</b> (mixed) .....	92 g/L
<b>Tack Free</b> , hrs .....	4 to 5
<b>Abrasion Resistance</b> , ASTM D 4060 .....	32 mg loss
<b>Tensile Strength</b> , ASTM D 638 psi (MPa) .....	5,500 (37.9)
<b>Tensile Elongation</b> , ASTM D 638 .....	15 to 30%
<b>Abrasion Resistance</b> , ASTM D 4060 .....	32 mg loss
<b>Flammability</b> , ASTM D 635 Self Extinguishing....	0.75 Max

---

## DIRECTIONS FOR USE

### SURFACE PREPARATION

The surface must be structurally sound, clean and free of grease, oil, curing compounds, soil, dust and other contaminants. See note in "Precautions/Limitations" section if coating is to be placed over old/existing epoxy or urethane coatings. New concrete and masonry must be at least 28 days old. Surface laitance must be removed. Concrete surfaces must be roughened and made absorptive, preferably by mechanical means, and then thoroughly cleaned of all dust and debris. The Concrete Surface Profile (CSP) should be equal to CSP 2-3 in accordance with Guideline 310.2R-2013, published by the International Concrete Repair Institute (ICRI). Allow substrate to dry before coating application. Following surface preparation, the strength of the surface can be tested if quantitative results are required by project specifications. An elcometer or similar tensile pull tester may be used in accordance with ASTM C1583, and the tensile pull-off strength should be at least 250 psi (1.7 MPa).

Do not apply epoxy or urethane coatings if there is excessive moisture in the concrete, or if the moisture vapor emission rate (MVER) is high. Before application of INCRETE HIGH PERFORMANCE EPOXY, perform either of these tests: ASTM F2170 - Standard Test Method for Determining Relative Humidity in Concrete Floor Slabs Using In-Situ Probes, or ASTM F1869 - Standard Test Method for Measuring Moisture Vapor Emission Rate of Concrete Subfloor Using Anhydrous Calcium Chloride. If the relative humidity is 70% or greater, or the MVER is 3 lbs/1000 ft<sup>2</sup> /24 hrs or greater, use a moisture mitigation system such as DURAL AQUATIGHT WB. After surface preparation and moisture testing, a test section application is recommended to confirm good adhesion and compatibility of the coating with the surface, and to confirm appearance and aesthetics. When coating steel, all contamination should be removed and the steel surface prepared to a "near white" finish (SSPC SP10) using clean, dry blasting media.

### MIXING

Mix INCRETE HIGH PERFORMANCE EPOXY using a low-speed drill and a mixing paddle. Pre-mix Part A and Part B separately for approximately 1 minute each. Combine Part A and Part B in a 2 to 1 ratio by volume, then mix thoroughly for 3 to 5 minutes. Scrape the bottom and sides of the containers at least once during mixing. Do not scrape bottom or sides of the container once mixing operations have ceased; doing so may result in unmixed resin or hardener being applied to the substrate. Unmixed resin or hardener will not cure properly. Do not aerate the material during mixing. To keep aeration to a minimum, the recommended mixing paddles are #P1 or #P2 as found in ICRI Guideline 320.5R-2014. If INCRETE HIGH PERFORMANCE EPOXY is used for INCRETE METAL FX, INCRETE GRANITE COAT, INCRETE CHROMA-QUARZ, or as a sand saturated epoxy bonding agent in the INCRETE LEVEL TOP SYSTEM, please consult the respective technical data sheet for proper installation instructions and coverages.

---

## PRECAUTIONS/LIMITATIONS

- Store at temperatures between 50 to 90 °F (10 to 32 °C).
- Do not aerate during mixing.
- Do not mix or apply unless surface, air, and material temperatures are 50 °F (10 °C) and rising.
- Do not apply if surface temperature is within 5 °F (-15 °C) of the dew point in the work area.
- Cure new concrete 28 days before application.
- Do not apply to slabs on grade unless a heavy uninterrupted vapor barrier has been installed under the slab.
- Do not apply if the floor is subject to moisture vapor drive or hydrostatic pressure.
- INCRETE HIGH PERFORMANCE EPOXY will yellow upon prolonged exposure to sunlight or high intensity artificial lights. For applications requiring color stability, urethane should be used as a topcoat.
- Although epoxy coatings are chemically resistant, the surface may stain after contact with some chemicals. A urethane topcoat is recommended for improved stain resistance.
- For professional use only.
- In all cases, consult the Safety Data Sheet before use.
- If used in INCRETE METAL FX, INCRETE GRANITE COAT or INCRETE CHROMA-QUARTZ, please consult the respective technical data sheet for proper installation instructions and coverages.

Rev. 07.21

---

**WARRANTY:** The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.