

HYDRO BAN® QUICK CURE WATERPROOFING

Refer to Data Sheets 670.4
9266-0001-2



A rapid, thin, liquid applied ready-to-use waterproofing membrane that is ANSI A118.10 Compliant. Featuring Wet-Cure technology, this allows curing even in humid, cold and damp environments. HYDRO BAN® Quick Cure allows for flood testing in as soon as 30 minutes* allowing contractors to install a shower system all in one day.

FEATURES/BENEFITS:

- Interior
- Shower pans, stalls and tub surrounds
- Thin; only 0.012" (0.3 mm) thick when cured
- Wet-Cure Technology — Can be used in humid, cold and damp environments.
- Allows for flood testing in 30 min. at 70°F (21°C) or higher*
- Bonds directly to metal, PVC and ABS plumbing fixtures
- Exceeds ANSI A118.10
- No solvents, non-flammable
- Eco-friendly, Low VOC

PACKAGING:

1 gal (3.8 L) Pail

HYDRO BAN CEMENTITIOUS WATERPROOFING MEMBRANE

Refer to Data Sheet 628.7
9259-0030-2



A one component, polymer fortified, cement based waterproofing material that mixes only with water. HYDRO BAN Cementitious Waterproofing Membrane handles negative and positive hydrostatic pressure up to 2 BARS (29 PSI (.2 MPa)) when applied at 40 MILS (1 mm) thick. Flood test within 2 hours. Passes ANSI A118.10 Waterproofing and ANSI A118.12 Crack Isolation (with mesh/fabric up to 1/8" (3 mm).

FEATURES/BENEFITS:

- Exterior
- Swimming pools, fountains, water features, spas and hot tubs
- Flood testing in 2 hours at 70°F (21°C) or higher*
- Can be used under pool plasters
- Bonds directly to metal, PVC and ABS plumbing fixtures
- Anti-fracture protection of up to 1/8" (3 mm)
- Exceeds ANSI A118.10 and A118.12 (with mesh) ISO 13007-5 CMP

PACKAGING:

30 lb (13.6 kg) Bag

Approximate Coverage

1 Gallon Unit: 134 ft²/gal (12.4 m²/3.8 L)

Approximate Coverage

At 40 mil (1mm) Thick - 120 ft² (11.2 m²)



* at 70°F (21°C) or higher.