



Sure Klean®

CLEANING & PROTECTIVE TREATMENTS

1260 Limestone & Marble Poultice

Sure Klean® 1260 Limestone & Marble Poultice is an easy-to-use low-odor paste poultice. It draws deep-seated oil, dirt, harmful salts and other embedded stains out of sensitive masonry, including polished limestone and marble.

Aided by special detergents and chelating agents, the moist poultice literally pulls contaminants out of the masonry pores and absorbs them into the paste. After a dwell time of 12-24 hours, the poultice and its captured contaminants are removed. Rinsing the cleaned surface with fresh water completes restoration of the masonry to its intended appearance.

Ready-to-use, non-acidic Sure Klean® 1260 Limestone & Marble Poultice is suitable for interior and exterior cleaning of horizontal, vertical and overhead surfaces.

ADVANTAGES

- Thoroughly cleans sensitive stone without etching or bleaching.
- Restores color and surface texture of polished and unpolished stone.
- Safe, low-odor non-acidic cleaning system, suitable for interiors or exteriors.
- Safe for most flooring and nearby surfaces.
- Ready-to-use paste requires no mixing.
- Highly “plastic” consistency makes uniform application easy and safe.

Limitations

- Cold adversely affects the cleaning properties of 1260 Limestone & Marble Cleaner. Wet paste freezes.

REGULATORY COMPLIANCE

VOC Compliance

Sure Klean® 1260 Limestone & Marble Poultice is compliant with all national, state and district VOC regulations.

TYPICAL TECHNICAL DATA

FORM	Grey paste, mild odor
SPECIFIC GRAVITY	1.14–1.26
pH	9–10
WT/GAL	9.5–10.5 lbs
TOTAL SOLIDS	30–35%
VOC CONTENT	not applicable
FLASH POINT	not applicable
FREEZE POINT	32° F (0° C)
SHELF LIFE	1 year in tightly sealed, unopened container

SAFETY INFORMATION

Always read full label and SDS for precautionary instructions before use. Use appropriate safety equipment and job-site controls during application and handling.

24-Hour Emergency Information:
INFOTRAC at 800-535-5053

Product Data Sheet

Sure Klean® 1260 Limestone & Marble Poultice

PREPARATION

Protect people, vehicles, property, painted surfaces, plants and all surfaces not meant for treatment from product, residue, rinse, splash and wind drift. Divert/protect pedestrian traffic.

Surface and Air Temperatures

Surface and air temperatures should be at least 50° F (10° C). Application when temperature is below freezing or will be overnight may harm masonry. If freezing conditions exist before application, let surface thaw.

Equipment

Apply with a plasterer's trowel or paste extrusion equipment suitable for high-volume extrusion of medium to heavy viscosity materials.

Before the poultice dries, cover it with PROSOCO's OverCoat protective paper, glossy side down, and tape down the edges. OverCoat is a semi-impermeable protective paper for keeping poultice

cleaners and paint remover moist, increasing effectiveness. The paper also protects cleaner and passersby from incidental contact. Visit www.prosoco.com or call 800-255-4255 for more information.

Scrape off dried or partially dried poultice with plasterer's trowels. Rinse the surface with clean water and sponges.

APPLICATION

Read "Preparation" and the Safety Data Sheet before use. **ALWAYS TEST** a small area of each surface to confirm suitability and desired results before beginning overall application. Test each type of masonry and each type of stain. Test with the same equipment, recommended surface preparation and application procedures planned for general application. Let test area dry 3-7 days before inspection and approval. Make the test panel available for comparison throughout the cleaning project.

Dilution

Apply as packaged. Do not dilute or alter.

Application Instructions

1. Apply paste to dry surface 1/8 to 1/4 inches thick using a trowel or airless sprayer or other suitable applicator.
2. Cover the poultice with PROSOCO's OverCoat, glossy side down. Press the OverCoat protective paper against the poultice. It will cling to the surface. Rub gently to remove air pockets and ensure smooth, overall adhesion. Tape/seal off edges of the paper.
3. Leave the covered poultice on the surface 12-24 hours.
4. Remove OverCoat. If still wet, let poultice dry 2-4 hours. The poultice surface develops cracks as it contracts and dries. A fully developed network of cracks indicates the poultice is completely dry.
5. Remove the poultice and captured contaminants. Insert a corrosion-resistant spatula, trowel or other suitable scraping device under the paste, and carefully lift from the surface. Remove as much residue as possible.
6. Rinse the surface thoroughly with fresh water, using a sponge, soft cloth or low-pressure/low-volume water-rinsing equipment.
7. Repeat application if needed.

Cleanup

Clean equipment with fresh water.

Recommended for these substrates. Always test. Coverage is in sq.ft./m. per gallon.			
Substrate	Type	Use?	Coverage*
Architectural Concrete Block	Burnished	yes	7-13 sq.ft. 0.6-1 sq.m.
	Smooth	yes	
	Split-faced	yes	
	Ribbed	yes	
Concrete	Brick	yes	7-13 sq.ft. 0.6-1 sq.m.
	Tile	yes	
	Precast Panels	yes	
	Pavers	yes	
	Cast-in-place	yes	
Fired Clay	Brick	yes	7-13 sq.ft. 0.6-1 sq.m.
	Tile	yes	
	Terra Cotta (unglazed)	yes	
	Pavers	yes	
Marble, Travertine, Limestone	Polished	yes	7-13 sq.ft. 0.6-1 sq.m.
	Unpolished	yes	7-13 sq.ft. 0.6-1 sq.m.
Granite	Polished	yes	7-13 sq.ft. 0.6-1 sq.m.
	Unpolished	yes	
Sandstone	Unpolished	yes	7-13 sq.ft. 0.6-1 sq.m.
Slate	Unpolished	yes	7-13 sq.ft. 0.6-1 sq.m.

*Applied 1/4 to 1/8 inch thick.
Always test to ensure desired results. Coverage estimates depend on surface texture and porosity.

Product Data Sheet

Sure Klean® 1260 Limestone & Marble Poultice

Maintenance

Freshly cleaned surfaces may be polished or sealed using appropriate products. No special treatments or procedures are necessary.

WARRANTY

The information and recommendations made are based on our own research and the research of others, and are believed to be accurate. However, no guarantee of their accuracy is made because we cannot cover every possible application of our products, nor anticipate every variation encountered in masonry surfaces, job conditions and methods used. The purchasers shall make their own tests to determine the suitability of such products for a particular purpose.

PROSOCO, Inc. warrants this product to be free from defects. **Where permitted by law, PROSOCO makes no other warranties with respect to this product, express or implied, including without limitation the implied warranties of merchantability or fitness for particular purpose.** The purchaser shall be responsible to make his own tests to determine the suitability of this product for

his particular purpose. PROSOCO's liability shall be limited in all events to supplying sufficient product to re-treat the specific areas to which defective product has been applied. Acceptance and use of this product absolves PROSOCO from any other liability, from whatever source, including liability for incidental, consequential or resultant damages whether due to breach of warranty, negligence or strict liability. This warranty may not be modified or extended by representatives of PROSOCO, its distributors or dealers.

CUSTOMER CARE

Factory personnel are available for product, environment and job-safety assistance with no obligation. Call 800-255-4255 and ask for Customer Care – technical support.

Factory-trained representatives are established in principal cities throughout the continental United States. Call Customer Care at 800-255-4255, or visit our website at www.prosoco.com, for the name of the PROSOCO representative in your area.

