

Product and Supplier Names

Maxxon® Gypsum Overspray Primer
 Maxxon Corporation
 920 Hamel Road · PO Box 253
 Hamel, MN 55340
www.Maxxon.com/123EZ · info@maxxon.com
 800-238-8461

Product Description/Use

Maxxon Gypsum Overspray is used as a primer over Maxxon Underlayments before the installation of glue down finished floor goods*.

*Where floor goods manufacturers require special adhesive or installation systems, their requirements supersede these recommendations.

FEATURES:

- Reduces porosity factor which allows proper open time for adhesive
- Enhances adhesive bond
- Adds strength and durability
- Increases abrasion resistance
- Low odor, Low VOC

Packaging

	1 Gallon Jug (3.8 L)	5 Gallon Pail (18.9 L)
Product number	13050	13061
Pre-Diluted?	Yes	No
Coverage per gallon (see yield chart)	300 ft ²	2,100 ft ²
Yield per container*	300 ft ²	10,500 ft ²

*Maxxon Gypsum Overspray is also available in 55 gallon and 275 gallon containers, undiluted. Contact Maxxon Customer Service for part numbers.

Yield Chart

Container Size	Application Rate		Total Parts after dilution		Gallons in container		Yield per Container
1 gal	300 ft ² per gallon of diluted mix	X	1 *	X	1	=	300 ft ²
5 gal			5		10,500 ft ²		
55 gal			55		300,755 ft ²		
275 gal			275		577,500 ft ²		

*prediluted

** 6-parts water, 1-part concentrate

Technical Data

Property..... Liquid
 Color..... White, dries transparent
 Optional blue, dries blue
 VOC Content.....0.02 g/L
 Nonvolatile Content 48% +/- 0.5
 Viscosity, Brookfield,
 RVF 25 °C 20 rpm, (cps) max..... 100 MPa
 Density.....1.01-1.02 g/mL (8.4-8.5 lb/gal)
 Glass Transition Temp..... +12 °C

Installation

TOOLS NEEDED: Mixing bucket, measuring tool, clean-potable water, 1/4" nap roller or spray tool

PREP: Before priming, test the underlayment for dryness. The underlayment must be fully dry before priming. Make sure substrate surface is broom cleaned, contaminant free and should have a smooth finish free from voids and sharp protrusions.

MIX RATIO: Do not dilute 1 gallon jugs; jugs are pre-diluted and ready for use. Five gallon and larger sizes must be diluted 6 parts water to 1 part concentrate.

APPLICATION: Roll or spray Maxxon Gypsum Overspray onto the floor at a rate of 300 ft² (27.9 m²) per gallon of mix.

For maximum results, Gypsum Overspray is applied about 1-2 hours prior to adhesive application.

Storage and Disposal

Keep from freezing; do not store below 40 °F (5 °C). Keep container closed when not in use. Keep in a dry, cool place.

Dispose of waste by following federal, state and local regulations. If spill occurs, clean up with potable water.

Warranty, Availability and Technical Services

See our website for complete warranty information. Technical performance verification and service is available through Maxxon Corporation or Maxxon Regional Representative throughout North America.