

# MasterTop® 1845 SRS CP

Methacrylate-based, self-leveling, flexible flooring system with pigmented smooth or slip resistant surface

FORMERLY DEGAFLEX™ CP

## YIELD

Primer: MasterTop SRS 41P with MasterTop SRS 103IN – 100 ft<sup>2</sup> (9.2 m<sup>2</sup>) / batch  
Self-Leveling Body Coat: MasterTop SRS 40TC – 40 ft<sup>2</sup> (3.7 m<sup>2</sup>) / batch @ 1/8" (3 mm)  
Top Coat: MasterTop SRS 53TC - 100 ft<sup>2</sup> (9.2 m<sup>2</sup>) / batch

All coverage rates are approximate. Coverage rates will vary with the desired texture and porosity of substrate.

## PACKAGING

MasterTop SRS 41P: 4.5 gallon (17 L) pail, 49 gallon (185 L) drum  
MasterTop SRS 40TC: 4.5 gallon (17 L) pail, 53.5 gallon (202.5 L) drum  
MasterTop SRS 53TC: 4.5 gallon (17 L) pail, 50 gallon (189 L) drum  
MasterTop SRS 103IN: 4.5 gallon (17 L) pail  
MasterTop SRS 100SL: 40 pound (18.41 kg) bag  
MasterTop SRS 100HD / Powder:  
Hardener: 2.5 pound (1.13 kg) bottle, 50 pound (22.7 kg) box  
MasterTop PGM 155: 10 pound (4.53 kg) pail

## COLOR

See Performance Flooring Color Chart for pigment

## SHELF LIFE

Resins: 2 years when properly stored

## STORAGE

Keep stored in cool, dry environment, and out of direct sunlight.

## VOC CONTENT

See MasterTop SRS LEED Letter

## DESCRIPTION

MasterTop 1845 SRS CP is a methyl-methacrylate (MMA), self-leveling flexible flooring system for use in areas that require a quick curing, decorative floor. The quick installation process makes this flooring system ideal for restaurants, public assembly facilities or processing facilities where minimal downtime is required. MasterTop 1845 SRS CP provides smooth or slip resistant impervious, seamless flooring system, where dirt and spills will remain on the surface, easily removed by most regular cleaning procedures. The surface of MasterTop 1845 SRS CP makes cleaning, decontamination, sanitation and sterilization fast and easy. Additionally, MasterTop 1845 SRS CP is a flexible flooring system with the ability to handle environments with temperature swings or exterior applications. The unique chemistry of the MasterTop 1845 SRS CP system provides a full cure in one hour or less for each component and provides a permanent chemical bond between each coat.

## PRODUCT HIGHLIGHTS

- Fully cures in one hour, reducing downtime for a quick return to service
- Seamless, impervious floor that is easy to sanitize, clean and maintain
- Excellent chemical resistance for a wide range of applications
- Flexible flooring system able to withstand temperature swings

## APPLICATIONS

- Used to resurface and coat concrete floors
- Use where aesthetics are a concern
- Exterior environments subject to freeze/thaw
- Pharmaceutical processing facilities
- "Back-of-the-house" restaurant applications
- Food processing facilities
- Public assembly facilities and stadiums
- Over de-glazed quarry tile

## LOCATION

- Interior and external flooring applications
- Applications subject to the freeze/thaw from exterior environments.

## SUBSTRATE

- Over new or existing concrete surfaces. When applying over other substrates, such as metal or tile, contact Master Builders Solutions Technical Service.

**TECHNICAL DATA**  
 TEST DATA

**MASTERTOP SRS 41P**

PROPERTY	RESULTS	TEST METHODS
<b>Percentage Reactive Resin</b>	100%	
<b>Percentage Solids</b>	100%	
<b>Water Absorption, (%/24 hours)</b>	0.06	ASTM D570
<b>Tensile Strength</b>	3,550 psi (24.5 MPa)	ASTM D638
Elongation @ Break	1.3%	ASTM D638
Tensile Modulus	2.1 x 10 <sup>5</sup> psi	ASTM D638
<b>Hardness (Shore D)</b>	75	ASTM D2240
<b>Viscosity</b>	15 – 25 cps	ASTM D2393
<b>Electrical Resistivity</b>	Vol: 2.5 x 10 <sup>15</sup> ohm/cm Surf: 8 x 10 <sup>12</sup> ohm	ASTM D257 ASTM D257

**MASTERTOP SRS 40TC**

PROPERTY	RESULTS	TEST METHODS
<b>Percentage Reactive Resin</b>	100%	
<b>Percentage Solids</b>	100%	
<b>Water Absorption, (%/24 hours)</b>	<0.1%	ASTM D570
<b>Tensile Strength</b>	1,350 psi (9.3 MPa)	ASTM D638
Elongation @ Break	140%	ASTM D638
<b>Hardness (Shore D)</b>	61	ASTM D2240
<b>Viscosity</b>	450 – 550 cps	ASTM D2393

**MASTERTOP SRS 53TC**

PROPERTY	RESULTS	TEST METHODS
<b>Percentage Reactive Resin</b>	100%	
<b>Percentage Solids</b>	100%	
<b>Water Absorption, (%/24 hours)</b>	0.05	ASTM D570
<b>Hardness (Shore D)</b>	80	ASTM D2240
<b>Viscosity</b>	300 – 400 cps	ASTM D2393
<b>Taber Abrasion Resistance</b> (mg. Loss, 1000 cycles, CS17 Wheel)	74	ASTM D4060

Chemical Resistance: Please refer to Master Builders Solutions Performance Flooring Chemical Resistance Guide

## HOW TO APPLY

Every MasterTop SRS flooring system is a multiple component system that utilizes a methyl-methacrylate (MMA) resin. It is critical that the instructions listed in the Safety Data Sheet and on the product label for every component of the system be read, understood and followed. MMA resins are flammable liquids in their uncured state. Smoking, open flames or sparks should not be permitted during the handling of the product. Explosion safe ventilation must be used during the application to minimize vapor collection in the installation area and to improve overall air quality for the crew. All foodstuffs must be removed during installation of the flooring system.

MasterTop SRS flooring systems are installed by approved contracting firms. The following is only a summary of the installation techniques used by MasterTop SRS approved contractors.

## SURFACE PREPARATION

1. Floors must be structurally sound and fully cured a minimum of 28 days. Test floor for vapor drive in accordance with ASTM D 4263, ASTM F 2170 or ASTM F 2420.
2. Repair concrete as necessary. If any patching is required, MasterTop 1817 SRS PC should be mixed and placed according to the MasterTop SRS Installation Guide.
3. Use a commercial degreaser to clean floors of oil, grease and other bond-inhibiting materials.
4. Remove curing and parting compounds and other surface hardeners and floor coatings in accordance with manufacturer's instructions.
5. Mechanical surface profiling is the method of surface preparation for both new and existing floors. Mechanically profile the floor to CSP-4 as described by the International Concrete Repair Institute. Do not use acid etching for surface preparation. Do not use any method that will fracture the concrete.
6. Bond tests should be performed once a small area has been mechanically profiled, so any adjustments can be made to the

surface preparation process. Bond tests should be repeated every 500 – 1,000 ft<sup>2</sup> (46.5 - 93 m<sup>2</sup>) Please refer to Bond Test Instruction Guide for further information.

7. Cracks wider than 1/16" (1.6 mm) should be "chased out" and opened during surface preparation. Any existing joints should be treated according to project specifications. Please refer to Joint Repair Guide for further information.
8. Areas around drains and other floor fixtures need to be ground and/or chipped to a depth between 1/2" – 3/4" (12.7 – 19 mm) and tapered back 3" – 6" (7.6 - 15.2 cm) away from drain (Refer to MasterTop SRS Detail Drawing 3.1).
9. Termination points should be saw cut to a depth of 1/4" (6.4 mm) and tapered back (Refer to MasterTop SRS Detail Drawing 3.2).

## MIXING

(Refer to MasterTop SRS Mixing Chart for exact batch sizes and measurements)

### MASTERTOP SRS 41P PRIMER

Measure resin and MasterTop SRS 103IN into pail and add proper amount of powder hardener. Mix with drill mixer for 15 – 30 seconds or until the powder hardener is completely dissolved.

### MASTERTOP SRS 40TC SL OVERLAY

Measure resin and pigment into a 5 gallon pail. Add 1 bag of MasterTop SRS 100SL powder and mix using a spiral mixing blade for 40 – 50 seconds, until a homogenous mixture is obtained. Add proper amount of powder hardener and mix for an additional 20 seconds.

### MASTERTOP SRS 53TC TOP COAT

Measure resin into pail and add proper amount of powder hardener. Mix with drill mixer for 15 – 30 seconds or until the powder hardener is completely dissolved. Note: After mixing, apply immediately. There will be 7 to 15 minutes of working time, depending on temperature.

## APPLICATION

### PRIMER

Apply the properly mixed MasterTop SRS 41P resin to the properly repaired concrete or properly prepared aged coating at approximately 100 ft<sup>2</sup> (9.3 m<sup>2</sup>) per batch. Allow primer to cure tack-free to an even, satin-like gloss and re-prime any dry spots.

### COVE BASE

If a cove base is to be installed, mix and apply according to the MasterTop SRS Cove Base Application Guide. Install cove base prior to installation of overlay coat.

### SCRATCH COAT

Any rough areas or depressions less than 1/4" (6.4 mm) should receive a scratch coat of MasterTop SRS 61BC with MasterTop SRS 100SL to smooth and level these areas. Any drips or ridges over 1/8" (3.2 mm) should be ground or sanded smooth. Allow to cure.

### OVERLAY COAT

Apply the properly mixed self-leveling MasterTop SRS 40TC overlay coat at 40 ft<sup>2</sup> per batch, at 1/8" (3.2 mm) thickness. A broadcast may be added at this time.

### TOPCOAT

Apply the properly mixed MasterTop SRS 53TC at approximately 100-125 square feet per batch. Allow to cure. The higher viscosity of MasterTop SRS 53TC makes it possible to apply only one topcoat.

## DRYING TIME

All components of the MasterTop 1845 SRS CP flooring system fully cure within one hour when properly installed.

## CLEAN UP

Clean tools as needed with inhibited MMA, acetone, ethyl acetate or similar solvents. Collect and dispose of all site wastes.

## MAINTENANCE

Regular cleaning and maintenance will prolong the life of all polymer flooring systems, enhance their appearance and

reduce any tendency to retain dirt. Follow the Master Builders Solutions Performance Flooring Cleaning and Maintenance Guide to maximize the life of the floor.

#### FOR BEST PERFORMANCE

- Not for use at application temperatures over 90° F (32° C).
- Not for use in areas exposed to strong solvents (consult Master Builders Solutions Technical Service).
- Install at recommended thickness to ensure proper curing and leveling.
- Topcoat must be back-rolled immediately to ensure uniform finish.
- Each application must be completely cured prior to the next application.
- Protect or remove food items prior to application to avoid any possible contamination.
- Use clean pails when mixing to avoid the possibility of improper curing.
- Proper air flow is critical to curing MMA materials. The use of fans is mandatory where air flow is restricted.
- Apply a bond test every 500 – 1,000 ft<sup>2</sup> (46.5 – 93 m<sup>2</sup>) prior to floor installation.
- Master Builders Solutions flooring specialists are available to assist you in the selection of the proper flooring system. Call 1-800-243-6739 for in-house and field technical assistance.
- Make certain the most current versions of product data sheet and SDS are being used; visit [www.master-builders-solutions.com/en-us](http://www.master-builders-solutions.com/en-us) to verify the most current versions.
- Proper application is the responsibility of the user. Field visits by Master Builders Solutions personnel are for the purpose of making technical recommendations only and not for supervising or providing quality control on the jobsite.

---

#### HEALTH, SAFETY AND ENVIRONMENTAL

Health, Safety and Environmental Read, understand and follow all Safety Data Sheets and product label information for this product prior to use. The SDS can be obtained by visiting [www.master-builders-solutions.com/en-us](http://www.master-builders-solutions.com/en-us), e-mailing your request to [mbsbcst@mbcc-group.com](mailto:mbsbcst@mbcc-group.com) or calling 1(800)433-9517. Use only as directed.

**IN CASE OF EMERGENCY: Call CHEMTEL +1 (800) 255-3924 or if outside the US or Canada, +1 (813) 248-0585.**

---

#### LIMITED WARRANTY NOTICE

Master Builders Solutions Construction Systems US, LLC (“Master Builders”) warrants this product to be free from manufacturing defects and to meet the technical properties on the current Technical Data Guide, if used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control. MASTER BUILDERS MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS. The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is shipment to purchaser of product equal to the amount of product that fails to meet this warranty or refund of the original purchase price of product that fails to meet this warranty, at the sole option of Master Builders. Any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. MASTER BUILDERS WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on Master Builders’ present knowledge and experience. However, Master Builders assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. Master Builders reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.

**FOR PROFESSIONAL USE ONLY. NOT FOR SALE TO OR USE BY THE GENERAL PUBLIC.**

