



Sika® Level-125

DURABLE, CEMENTITIOUS, SELF-LEVELING UNDERLAYMENT

- Economical self-leveling
- Easy to mix and apply
- Level new and old floors

Available in
50 lb. Bag



BUILDING TRUST



Sika® Level-125

DURABLE, CEMENTITIOUS, SELF-LEVELING UNDERLAYMENT

WHERE TO USE

- Colleges
- Corridors
- Domestic properties
- Galleries
- Hotels
- Hallways

FEATURES AND BENEFITS

- Easy and quick to install
- Zero VOC content and low odor
- Pumpable self-leveling
- Excellent bonding performance
- Suitable for non-moisture subfloor after 2-3 hours
- Apply floor coverings after 1-3 days

NOTE: Always refer to current PDS and SDS for detailed performance specifications prior to use.

TYPICAL DATA (Material and curing conditions @ 73°F (23°C) and 50% R.H.)

Color	Concrete Gray
Application Thickness	1/8" up to 2" (3 mm up to 51 mm)
Density (ASTM C185)	133 lbs/cu.ft.
Working Time	Approx. 25 minutes
Ready for Foot Traffic	2 - 3 hours
Flexural Strength (ASTM C348)	1,150 psi (8 MPa) at 28 days
Compressive Strength (ASTM C109)	4000 psi (28 MPa) at 28 days
VOC (EPA METHOD 24)	0 g/l

Sika® Classification Chart

Strength					
Flow					
Depth					
Speed					



FOR MORE INFORMATION:

Contact Sika: Phone 800.933.SIKA(7452) Website: www.sikasecure.com

Sika Corporation
 201 Polito Avenue
 Lyndhurst, NJ 07071
 Phone: 201-933-8800
 Fax: 201-933-6225



BUILDING TRUST

