



INCRETE JET PHOS

CONCRETE CLEANER, RUST REMOVER AND METAL PRIMER **EUCLID CHEMICAL**

PACKAGING

1 gal (3.8 L) units

APPEARANCE

Clear liquid

CLEAN UP

Flush with water. Neutralize with baking soda and water if needed.

SHELF LIFE

3 years in original, unopened container

BRIEF OVERVIEW

INCRETE JET PHOS is a superior acidic cleaner for concrete, pavers and stone; as well as a rust/efflorescence remover. INCRETE JET PHOS can also be used as a primer for iron and steel.

PRODUCT CHARACTERISTICS

ADVANTAGES

- Works on all cementitious surfaces
- Removes efflorescence stains on brick and decorative pavers, new concrete and stone construction, as well as secondary efflorescence on concrete block.
- Improves color uniformity and enhances appearance
- Contains no muriatic acid
- Removes rust stains
- Metal primer for all ferrous metals

COMMON USES

- Concrete cleaner
- Rust remover
- Ferrous metal primer

COMMON APPLICATION METHODS

- Masonry brush
- Low-pressure sprayer

DIRECTIONS FOR USE

FOR FERROUS METAL PRIMING

RUSTED METAL

INCRETE JET PHOS is a metal primer, not a paint. You do not have to remove the rust. INCRETE JET PHOS causes iron oxide (rust) to chemically change to iron phosphate - an inert, hard substance that turns the metal black. Remove loose scale, dirt, and other accumulation with a wire brush. Apply a coat of INCRETE JET PHOS. Let stand overnight, and then apply paint. If surface is greasy or oily, clean with mineral spirits before applying INCRETE JET PHOS. Where rust is heavy, two coats of INCRETE JET PHOS may be necessary to thoroughly penetrate and blacken the surface to be painted. A dry, powdery, grayish, white surface usually develops, indicating that INCRETE JET PHOS has reacted with the metal. The powder is harmless, but any excess should be brushed off before painting.

NEW METALS

For new ferrous, aluminum, or galvanized surfaces, remove dirt, grease, oil, and apply INCRETE JET PHOS. Let dry overnight, and then apply paint. When applied to a rusted surface, INCRETE JET PHOS chemically changes iron phosphate, a hard substance that turns the metal black. A finish coat will last twice as long after an application of INCRETE JET PHOS because subsequent paint coating attaches itself so tightly that moisture and oxygen cannot attack the metal.

DIRECTIONS FOR USE CONT.

FOR CONCRETE, PAVER AND STONE CLEANING

PREPARATION

Protect surfaces, plants and other non-cementitious materials from product, residue, rinse, overspray, and fumes. For best results, clean when air and surface temperatures are 40° F (4° C) or above. Apply with acid resistant sprayers and brushes. Apply a test area to confirm desired results and proper dilution rate before beginning full scale application.

DILUTION

Testing will indicate the proper dilution.

Standard dilution is 1 part INCRETE JET PHOS : 6 parts water for mild cleaning and efflorescence removal. Use a concentration of up to 1 INCRETE JET PHOS : 2 parts water for rust stain removal. Always pour cold water into empty bucket first, then carefully add INCRETE JET PHOS. Do not use hot water. Use plastic, acid resistant, buckets only.

APPLICATION

1. Wet surface with clean water. For vertical surfaces, keep lower areas damp to avoid streaks.
2. Apply diluted INCRETE JET PHOS directly to surface with acid resistant masonry brush or low-pressure spray.
3. Allow INCRETE JET PHOS to dwell on the surface for 5 minutes or until stains are gone. Do not allow to dry on the surface.
4. Reapply as needed and rinse thoroughly with fresh clean potable water.

For best results work from the bottom to the top, and brush while rinsing to remove all residue.

PRECAUTIONS/LIMITATIONS

- INCRETE JET PHOS contains Phosphoric Acid.
- Not to be taken internally.
- Prolonged exposure causes skin irritation.
- Use rubber gloves and eye protection.
- if splashed in eye, skin, or clothing, flush immediately with water.
- For professional use only.
- In all cases, consult the Safety Data Sheet before use.

Rev. 07.21

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.