PRODUCT DATA SHEET



DESCRIPTION

Available in both flat and tapered panels. Closed-cell polyisocyanurate (polyiso) foam core integrally bonded to inorganic coated glass facers (CGF) on both sides. ACFoam®-III is offered in a variety of thicknesses (including tapered insulation), providing long-term thermal resistance (LTTR) values from 5.7 (4.3 for tapered) to 26.8. Flat ACFoam-III is available in 4ft x 8ft (1220mm x 2440mm) and 4ft x 4ft (1220mm x 1220mm) panels. Tapered ACFoam-III is available in 4ft x 4ft (1220mm x 1220mm) panels. Manufactured in accordance with **ASTM C1289, Type II, Class 2, Grade 2 (20 psi) or Grade 3 (25 psi) and CAN/ULC-S704 Type 2, Class 3 or Type 3, Class 3.**

APPLICATIONS

Manufactured and tested for use in new and re-roofing applications. ACFoam-III roof insulation shall be installed over the roof deck. ACFoam-III is used in built-up (BUR), modified bitumen, standing seam metal, ballasted single-ply, mechanically attached single-ply and adhered single-ply roofing systems. These roofing systems depend on proper installation for successful performance. Refer to roof cover manufacturer, FM Approvals® RoofNav and UL Product iQ® for additional application details.

INSTALLATION

ACFoam-III shall be kept dry before, during and after installation. This product will burn if exposed to an ignition source of sufficient heat and intensity. Do not apply flame directly to ACFoam-III insulation. Refer to product packaging, Atlas Technical Bulletin #109 for storage and handling recommendations. To minimize the effect of thermal bridging, and the impact of moisture/airflow into the roof system, Atlas strongly recommends the ACFoam-III be installed in multiple layers. Please reference the ACFoam Fastening Pattern Guide for General Installation, Usage Instructions, and Warranty information for ACFoam products. Typical field fastening requirements can be obtained from roof cover manufacturer and/or,FM Approvals Roof Nav, or FM Global Property Loss Prevention Data Sheet 1-29.

Prior to installation, Atlas Roofing Corporation recommends, as applicable, you consult with your local building code official(s), contract documents, design professional, and all other relevant parties to ensure appropriate compliance.

PHYSICAL PROPERTIES	ACFOAM-III MEETS OR EXCEEDS THE	II MEETS OR EXCEEDS THE FOLLOWING PHYSICAL PROPORTIES						
PROPERTY	TEST METHOD	ASTM C1289 OR CAN/ULC S704 (MIN REQUIREMENTS)						
DIMENSIONAL STABILITY	ASTM D2126	<2%						
COMPRESSIVE STRENGTH	ASTM D1621	20 psi (140 kPa) or 25 psi (172 kPa)						
WATER ABSORPTION	ASTM C209 ASTM C1763 ASTM D2842	<1.5% <1.5% <3.5%						
WATER VAPOR TRANSMISSION	ASTM E96	<4.0 perm (228.8ng/(Pa*s*m²))						
PRODUCT DENSITY	ASTM D1622	Nominal 2.0 pcf (32.04 kg/m³)						
FLAME SPREAD	ASTM E84/UL723	⁻ 40–60						
SMOKE DEVELOPMENT	ASTM E84/UL723	·50 – 170						
TENSILE STRENGTH	ASTM D1623	>730 psf (35 kPa)						
SERVICE TEMPERATURE	-	-100° to +250°F						

"Numerical ratings are not intended to reflect performance under actual fire conditions. Flame spread index of <75 and smoke development <450 meet code requirements for foam plastic roof insulation. Physical properties listed above are presented as typical average values as determined by referenced ASTM test methods and are subject to nominal manufacturing variations.

CODE COMPLIANCE

- ASTM C1289 Type II, Class 2, Grade 2 (20 psi) or Grade 3 (25 psi)
- CAN/ULC-S704, Type 2, Class 3 or Type 3, Class 3
- CCMC No. 12423-L
- UL Certified for Canada Insulated Roof Deck Assemblies Construction No. C38 and 52. Meet CAN/ UIC-S126. CAN/UIC-S101 and CAN/UIC-S107
- UL 1256 Classification Construction No. 120, 123 & 292
- UL 790 (ASTM E108) Roofing Systems Classification
- UL 263 (ASTM E119) Fire Resistance Classification
- FM 4450/4470 Refer to FM Approvals® RoofNav for Specific System Details
- IBC Chapter 26 & NBC Sections on Foam Insulation
- California State Thermal Insulation Directory, T1231
- Miami-Dade, NOA No. 17-1211.05
- Florida Product Approval, No. FL17989
- GREENGUARD GOLD Certified
- UL 2824 Resistant to Mold Growth as Validated by UL Environment





FLAT CGF ROOF INSULATION

THICKNESS	THERMAL RESISTANCE		PIECES	SQUARE FEET Per Unit		TRUCKLOAD	AVERAGE	RECYCLED CONTENT			
IHICKNE99	AVERAGE 1LTTR VALUE	²RSI	PER Unit	4×8	4×4	QUANTITIES (SQUARES)	WEIGHT (LB/SF)	POST Consumer	PRE Consumer	TOTAL	
1.0"	5.7	1.00	48	1536	768	368.64	0.315	-	6.2%	6.2%	
1.5"	8.6	1.50	32	1024	512	245.76	0.383	-	7.7%	7.7%	
2.0"	11.4	2.01	24	768	384	184.32	0.450	-	8.7%	8.7%	
2.5"	14.4	2.53	19	608	304	145.92	0.518	-	9.4%	9.4%	
3.0"	17.4	3.06	16	512	256	122.88	0.585	-	10.0%	10.0%	
3.5"	20.5	3.60	13	416	208	99.84	0.653	-	10.5%	10.5%	
4.0"	23.6	4.15	12	384	192	92.16	0.720	-	10.9%	10.9%	

TAPERED CGF ROOF INSULATION

SLOPE	LABEL	THICKNESS			THERMAL RESISTANCE		BOARD	PIECES	BOARD	SQUARE	WEIGHT	RECYCLED CONTENT		
		MINIMUM	MAXIMUM	AVERAGE	AVERAGE 'LTTR VALUE	²RSI	FT PER PIECE	PER Unit	FT PER Unit	FT PER Unit	(LB/SF)	POST CONSUMER	PRE Consumer	TOTAL
1/8"	AA	0.5"	1.0"	0.75"	4.3	0.76	12	64	768	1024	0.281	-	5.2%	5.2%
1/8"	А	1.0"	1.5"	1.25"	7.1	1.25	20	38	760	608	0.349	-	7.0%	7.0%
1/8"	В	1.5"	2.0"	1.75″	10.0	1.76	28	26	728	416	0.416	-	8.2%	8.2%
1/8"	C	2.0"	2.5"	2.25"	12.9	2.27	36	20	720	320	0.484	-	9.1%	9.1%
1/4"	Χ	0.5"	1.5"	1.0"	5.7	1.00	16	48	768	768	0.315	-	6.20%	6.20%
1/4"	Υ	1.5"	2.5"	2.0"	11.4	2.01	32	24	768	384	0.450	-	8.68%	8.68%
1/2"	Q	0.5"	2.5"	1.5"	8.6	1.51	24	32	768	512	0.383	-	7.66%	7.66%

¹LTTR (long term thermal resistance) values were determined in accordance with CAN/ULC-S770. Test samples were third-party selected and tested by an accredited material testing laboratory.

FOR A COMPLETE LIST
OF PRODUCT SIZES,
SCAN OR CLICK QR CODE
TO DOWNLOAD THE
PACKAGE & LOADING GUIDE



WARRANTY

ACFoam-III is backed by a Limited 20-Year Thermal Warranty. For complete terms and conditions, visit roof.atlasrwi.com/warranty

Other than the aforementioned representations and descriptions, Atlas Roofing Corporation (hereafter, "Seller") makes no other representations or warranties as to the insulation sold herein. The Seller disclaims all other warranties, express or implied, including the warranty of merchantability and the warranty of fitness for a particular purpose. Seller does, however, have a limited warranty as to the LTTR-Value of the insulation, the terms of which are available upon request from the Seller. Seller shall not be liable for any incidental or consequential damages including but not limited to the cost of installation, removal, repair or replacement of this product. Buyer's remedies shall be limited exclusively to, at Seller's option, the repayment of the purchase price or resupply of product manufactured by Atlas in a quantity equal to that of the nonconforming product. Atlas distributors, agents, salespersons or other independent representatives have no authority to waive or alter the above limitation of liability and remedies.



Atlas Roofing Corporation

2000 Riveredge Parkway, Suite 800 • Atlanta, GA • 30328 770-952-1442 • roof.atlasrwi.com



²RSI is the metric expression of R-value (m² • K/W).

To minimize the effects of thermal bridging, and the impact of moisture/airflow into the roof system, Atlas strongly recommends the ACFoam insulation assembly be installed in multiple layers.