



EUCLID CHEMICAL

EPOXY PRODUCTS USAGE

Product	Viscosity (cp)	ASTM C881 Bonding		Crack Repair			Anchoring & Doweling	Surface Healer-Sealer	Precast Segment Adhesive	Patching/ Repair Mortar	ASTM C881		
		Hardened Concrete to Hardened Concrete	Fresh Concrete to Hardened Concrete	Capping Gel	Pressure Injection	Gravity Feed					Type(s)	Grade	Class(es)
Dural 452 Gel	Non-Sag	✓	✓	✓			H, V			H, V	I, II, IV, V	3	C
Dural 452 LV	350	✓			✓	✓				H	I, IV,	1	C
Dural 452 MV	3,700	✓	✓				H			H, V	I, II, IV, V	2	C
Dural HS Gel	Non-Sag	✓	✓	✓			H, V				I, II, IV, V	3	A, B, C
Dural Fast Set Gel	Non-Sag	✓		✓			H, V			H, V	I, IV,	3	B, C
Dural Fast Set LV	500	✓			✓	✓				H	I, IV,	1	A, B, C
Dural Injection Gel	Non-Sag	✓	✓	✓	✓					H, V	I, II, IV, V	3	C
Dural 335	80 to 100	✓				✓		✓			I, IV	1	B, C
Dural LPL MV	3,400		✓							H	II	2	C, E, F
Dural 100	Non-Sag	✓							✓		VI	3	D, E, F
Dural 106	Non-Sag	✓							✓		VI	3	D, E, F
Duralflex Gel	Non-Sag									H, V	III	3	B, C
Duralflex LV	1,800									H	III	1	B, C

KEY

H = Horizontal Substrate

V = Vertical Substrate

* Classes A & B only